

NL1A Values

cenovus
ENERGY

FITTING/VALVE TRANSFER PULL SHEET

SIZE	#	ITEM DESCRIPTION	Body Heat #	MOD# Bonnet Heat #	DATE: TAG #	MT #	SN#	PO# / ITEM #
8	300	Gate Valve	A60620	A60620	9-GF-03A00	KF813100-366	-348	NL1A-2001/51
"	"	"	A60624	A60713	"		-348	"
"	"	"	A60624	A60624	"		-348	"
"	"	"	A60624	A60620	"		-362	"
6	150	Check Valve	722V36	132721A	GF-01A00	M/0-06-052RF8		NL1A-2005B/8
6	600	Gate Valve	V18106	V18052	GF-06L00	2473/9		NL1A-2001/94
"	"	"	V18106	V18218	"		/11	"
A00.002	6	Gate Valve	BND01C06	BNC04G02	GF-03A00	8515-000		NL1A-2001/36
"	10	Gate Valve	F3711	F3825	GF-03A00	50421-1030-2		NL1A-2001/129
"	"	"	F3857	F3827	"		-3	"
A00.007	8	300	7L394	76H22	GF-03A00	44132-120-19		NL1A-2001/125
"	"	"	010L3	91241	"	48082-301-11		"
"	10	Gate Valve	F0960	F2443	GF-03A00	47219-180-2		NL1A-2001/157
"	"	"	F0191	F2755	GF-03A00		-3	"
A01.101	6	300	Gate Valve	BND14G15	GF-03A00	N/A		NL1A-2001/36
"	"	"	BND17A06	BND04C09	"	N/A		"
A00.007	3	300	Gate Valve	1H795	TF-03A00	38026-220-19		NL1A-2001/92
"	"	"	214078	3H732	"		-3	"
A00.002	"	"	90063	3H733	"		-12	"
A01.101	12	150	Gate Valve	A60634	GF-01A00	KF81300-352		NL1A-2001/55
"	"	"	A60632	A60632	"		-351	"
A01.101	10	150	Gate Valve	73CJB	GF-01V00	TNC-3689-011		NL1A-2000B/11
"	"	"	72MJB	71RT6	"			"
"	8	150	Gate Valve	5H392	GF-01A00	37685-050-339		NL1A-2001/149
"	6	150	"	BNE55C02	GF-01L00	8515-001		NL1A-2001/147
"	4	300	"	1H736	GF-03A00	36582-350-9		NL1A-2001/146
"	3	300	Gate Valve	BNC31H21	TF-03A00	N/A		NL1A-2001/65
"	"	"	"	"	"			"
2	300	Gate Valve	716H2	640H4	GF-03500	48489-360-21		NL1A-2001/89
2	300	Gate Valve	32973	581H9	"		-3	"
"	"	"	692H0	578H7	"		-16	"
A00.002	"	"	615H5	708H6	"		-1	"

N/L1A Valves.

cenovus
ENERGY

FITTING/VALVE TRANSFER PULL SHEET

SIZE	#	ITEM DESCRIPTION	Body Heat #	MOD# Bonnet Heat #	DATE: TAG #	MT #	SN#	PO# / ITEM #
A00.003	8	Gate Valve	A14405	A14414	GF-01A00		ZF166/49	N/L1A-2001/13
	300	Gate Valve	A60620	A60620	GF-03A00		KF813110005	N/L1A-2001/51
A01.101	2	"	A60711	A60624	"		KF813110006	"
	6	Gate Valve	BND13C15	BND17H29	GF-03A00		N/L1A	N/L1A-2001/36
A00.007	1	"	BND16C12	BND15C14	"		"	"
A01.101	6	Gate Valve	BND02C24	BND06C28	GF-01A00		8515-001	N/L1A-2001/49
	3	150	X2880	X1725	GF-01L00		53001-040-1	N/L1A-2001/120
A00.007	11	"	X2880	X1725	"		-4	"
A01.101	11	"	BND32E17	BND04E28	GF-01A00		8512-001	N/L1A-2001/44
	6	Gate Valve	BND04L10	BND09B02	GF-03A00		8515-000	N/L1A-2001/20
A00.007	2	150	678H3	05028	GF-01A10		48469-790-139	N/L1A-2001/115
	300	"	87326	93184	GF-03A00		52147-630-42	N/L1A-2001/116
	3	150	80289	46972	GF-01A00		52147-580-38	N/L1A-2001/118
	2	150	BND54F10	BND51E02	GF-01L00		8510-002	N/L1A-2001/144
A01.101	3	150	X2880	X1725	GF-01L00		53001-040-2	N/L1A-2001/145
	11	"	X2880	X1725	"		-3	"
A00.007	2	150	BND54F10	BND54F11	GF-01L00		8510-001	N/L1A-2001/78
	2	150	Gate Valve	41L41	GF-01A00		48489-790-85	N/L1A-2001/156
A02.201	"	"	BND51L27	BND51L29	GF-01L00		N/L1A	N/L1A-2001/157
	"	"	BND53M10	BND52L28	"		N/L1A	"
A00.002	3	300	Gate Valve	ZH078	TF-03A00		38026-220-18	N/L1A-2001/92
	11	"	ZH106	99U10	"		-16	"

Certificate #: P4-128759

Page 1 of 2

07.1.2015

Fax: 450-378-6865

Hydro Test Spec: MSS-SP61/B16.34

Test Result: ACCEPTABLE

MATERIAL TEST RESULTS SHOWN BELOW:

CHEMICALS

ASTM Code: A216-08-WCB-

MECHANICALS [F/B: Fatening/ bending; GS: Grain size]

Description : VALVE 3" 300 GLOBE RF

REV

NONE

Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC021.27	BONNET	0.192	0.926	0.028	0.011	0.471	0.040	0.045	0.036	0.006	0.007	558.0 / 80.9	351.0 / 50.9	29.8	57.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC031.27	BONNET	0.192	0.891	0.032	0.011	0.436	0.041	0.080	0.043	0.004	0.007	599.0 / 86.9	408.0 / 59.2	28.6	54.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC031.28	BONNET	0.207	0.908	0.030	0.009	0.436	0.028	0.054	0.032	0.004	0.007	571.0 / 82.8	371.0 / 53.8	28.8	54.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC031.10	BONNET	0.195	0.862	0.031	0.010	0.437	0.037	0.050	0.050	0.007	0.007	558.0 / 80.9	395.0 / 57.3	29.2	57.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC17A07	BONNET	0.192	0.897	0.028	0.011	0.410	0.035	0.024	0.033	0.002	0.008	562.0 / 81.5	334.0 / 48.4	28.4	53.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC22H19	BODY	0.201	0.954	0.017	0.013	0.478	0.042	0.045	0.052	0.006	0.007	563.0 / 81.7	363.0 / 52.6	30.4	58.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC24H17	BODY	0.193	0.954	0.030	0.009	0.442	0.036	0.063	0.052	0.005	0.008	546.0 / 79.2	346.0 / 50.2	29.0	57.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		

VELAN

Certificate of Conformance

Page 2 of 2
Certificate #: P4-128759

Heat Code	Desc	(C)	(Ma)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
BNC251H04	BODY	0.191	0.902	0.024	0.007	0.455	0.045	0.057	0.043	0.005	0.012	563.0 / 81.7	363.0 / 52.6	27.2	46.0	/
Heat Treatment																
NORM ALIZED																
Heat Code	Desc	(C)	(Ma)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
BNC30H22	BODY	0.201	0.934	0.033	0.014	0.452	0.048	0.042	0.087	0.010	0.008	558.0 / 80.9	359.0 / 52.1	29.2	57.0	/
Heat Treatment																
NORM ALIZED																
Heat Code	Desc	(C)	(Ma)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
BNC31H21	BODY	0.201	0.926	0.030	0.010	0.501	0.078	0.066	0.049	0.018	0.009	567.0 / 82.2	367.0 / 53.2	27.8	52.0	/
Heat Treatment																
NORM ALIZED																
Heat Code	Desc	(C)	(Ma)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
BNC32H21	BODY	0.199	0.896	0.024	0.011	0.456	0.041	0.059	0.051	0.006	0.006	571.0 / 82.8	379.0 / 55.0	29.0	56.0	/
Heat Treatment																
NORM ALIZED																

Velan hereby certifies that the valve(s) described above is (are) in conformance with the purchase order and specification requirements. The test report represents the actual attributes of items furnished and all test results are in full conformance with applicable specification and purchase order requirements.

for
Manager of Q.C. Documentation
Date
30-JAN-2013

Customer Representative
Date

ELI

NELIA-DRH-20001

PO# 675

IF-03A00



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 48489-360(80252017)
DATE: 2014-1-21
PAGE: 1 OF 3

CUSTOMER

NEWAY VALVE INTERNATIONAL, INC-MRM
9757 Stafford Centre Rd., Stafford
USA
USA

QUANTITY

PART NO.

PRODUCT CODE

PRODUCT DESCRIPTION

1

10208531

2G3RA12-NC-000

GATE VALVE 2G3R, C00/12
I-LCC-WEB, -B7M/2H/M
GATE VALVE 2, 300LB
ASTM A216 WCB, F316/HF
RAISED FACE END/LOW EMISSION

PURCHASE ORDER:

6003239MRC_S 78H 218

PRESSURE TEST (Mpa/PSI)

OTHER INSPECTION

PROJECT NAME:	HYDROSTATIC		PNEUM		RESULT	VISUAL	DIMENSION	OPERATION	MARKING
	SHELL	SEATS/BACKSEAT	SEATS						
	7.8/1131	5.7/827	0.6/87		OK	OK	OK	OK	OK

APPLICABLE STANDARDS AND SPECIFICATION:

- P/T RATING: ASME B16.34
- MAIN MATERIAL: RELEVANT ASTM STANDARD
- DESIGN: API600 ASME B16.34
- TEST: API598 EN12266
- TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL
- VALVES CONFORM TO NACE STANDARD MR 0175 LATEST REVISION

NOTE: ALL RELATED STANDARDS ARE THE LATEST VERSION.

NU1A-DPH-2001
CPO# 89
CF-03500

WITNESSED BY: _____

Q.C. Manager

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order.

NEWAY VALVE



MATERIAL TEST REPORT

ISO EN 10204 2004-3.1

TC No. 48489-360(80252017)

DATE: 2014.1.21

PAGE: 2 OF 3

PRODUCT TRACEABILITY

[illegible]



MATERIAL TEST REPORT

ISO EN 10204 2004-3.1

TC NO. 48489-360(80252017)

DATE: 2014.1.21

PAGE: 3 OF 3

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace
WCB	NORMALIZE	920-940 (1688-1724°F)	1H/25MM	AIR	GAS

We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS														MECHANICAL PROPERTIES						IMPACT TEST (Joule)
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD		
			%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%		HB	TEMP °C		
		MAX	0.23	1.28	0.6	0.03	0.035	0.5	0.5	0.2	0.3	0.03				655				237			
		MIN														485	250	22	35	135			
WEDGE BODY BONNET	WCB	31A71	0.22	0.81	0.45	0.011	0.016	0.107	0.05	0.011	0.018	0.001				0.383	510	345	30	45	174		
	WCB	3L973	0.205	1.035	0.407	0.016	0.025	0.057	0.039	0.005	0.029	0.005				0.395	490	315	32	68	188		
	WCB	581H9	0.208	1.07	0.402	0.012	0.032	0.034	0.016	0.007	0.032	0.002				0.398	625	400	33	53	167		



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 48489-360(80252017)
DATE: 2014-1-21
PAGE: 1 OF 3

CUSTOMER
NEWAY VALVE INTERNATIONAL, INC.-MRM
9757 Stafford Centre Rd., Stafford
USA
USA

QUANTITY
1
PART NO.
10209531
PRODUCT CODE
2G3RA12-NC-000
PRODUCT DESCRIPTION
GATE VALVE, 2G3R, C0012
(LLC-WEB, -B7M/2HM)
GATE VALVE, 2, 300LB
ASTM A218 WCB, F316HF
RAISED FACE END, LOW EMISSION

PURCHASE ORDER:

6003239MRC_S 78H 218

PROJECT NAME:

PRESSURE TEST (Mpa/PSI)			OTHER INSPECTION			
HYDROSTATIC		PNEUM	RESULT	VISUAL	DIMENSION	OPERATION
SHELL		SEATS/BACKSEAT	SEATS	OK	OK	OK
7.8/1131		5.7/827	0.8/87			

APPLICABLE STANDARDS AND SPECIFICATION:

- P/T RATING: ASME B16.34
- MAIN MATERIAL: RELEVANT ASTM STANDARD
- DESIGN: API600 ASME B16.34
- TEST: API598 EN12266
- TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL
- VALVES CONFORM TO NACE STANDARD MR.0175 LATEST REVISION

NOTE: ALL RELATED STANDARDS ARE THE LATEST VERSION.


WITNESSED BY: _____

Q.C. Manager

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order.

NEWAY VALVE

Signature
Date



ISO EN 10204 2004-3.1


TC No. 48489-360(80252017)

DATE: 2014.1.21

PAGE: 2 OF 3

PRODUCT TRACEABILITY

Address: No. 999 Xinjiang Road Suzhou New District, China Tel: 86-512-666-51365 Fax: 86-512-666-51360 <http://www.newayvalve.com>



We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS														MECHANICAL PROPERTIES										IMPACT TEST (J/INCH)		
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD								
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%		HB	TEMP °C	Avg	Min					
			MAX 0.23	1.28	0.6	0.03	0.035	0.5	0.5	0.2	0.3	0.03				665				237									
			MIN													485	250	22	35	135									

Address: No. 999 Xinagjiang Road Suzhou New District, China Tel: 86-512-6666-51365 Fax: 86-512-6666-51360 <http://www.newayvalve.com>

0A.2



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 48489-360(80252071)
DATE: 2014-1-21
PAGE: 1 OF 3

CUSTOMER

NEWAY VALVE INTERNATIONAL, INC-MRM
9757 Stafford Centre Rd., Stafford
USA
USA

QUANTITY

1

PART NO.

10209531

PRODUCT CODE

2G3RA12-NC-000

PRODUCT DESCRIPTION

GATE VALVE 2G3R, C00/12
[L-LLC-WEB-B7M/2HM]
GATE VALVE, 2.390LB
ASTM A216 WCB, F316/HF
RAISED FACE END, LOW EMISSION

PURCHASE ORDER:

6003239MRC_S 78H 218

PRESSURE TEST (Mpa/PSI)

OTHER INSPECTION

PROJECT NAME:	HYDROSTATIC		PNEUM		RESULT	VISUAL	DIMENSION	OPERATION	MARKING
	SHELL	SEATS/BACKSEAT	SEATS		OK	OK	OK	OK	OK
	7.8/1131	5.7/827	0.6/87						

APPLICABLE STANDARDS AND SPECIFICATION:

- P/T RATING: ASME B16.34
- MAIN MATERIAL: RELEVANT ASTM STANDARD
- DESIGN: API600 ASME B16.34
- TEST: API598 EN12286
- TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL
- VALVES CONFORM TO NACE STANDARD MR.0175 LATEST REVISION

NOTE: ALL RELATED STANDARDS ARE THE LATEST VERSION.

WCL1A-DPH-2001
CF-03500
PC# 89

WITNESSED BY: _____

Q.C. Manager

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order.

NEWAY VALVE




MATERIAL TEST REPORT

ISO EN 10204 2004-3.1

TC No. 48489-360(80252017)
DATE: 2014.1.21
PAGE: 2 OF 3

PRODUCT TRACEABILITY

[illegible]



ISO EN 10204 2004-3.1

We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.

Address: No. 999 Xinagjiang Road Suzhou New District, China Tel: 86-512-6666-51365 Fax: 86-512-6666-51360 <http://www.newwayvalve.com>

John H.

Page 1 of 2



Inspection Certificate and Material Test Report
(EN10204-1991 3.1.B / EN10204-2004 3.1)

DSI Valve Solutions
12735 Dairy Ashford
Stafford TX 77477
281-637-2000 - Fax 281-637-2299
www.dsivalve.com

Certificate/Serial/Job No:

ZH73 / 11

Quality Department:

John

Quantity	Size (NPS)	Class	Product	Description	Type	SONumber	Line	Sold to	Date
2	6	600	/	103249 DSI 66LUF-N-LCC	GATE				8/23/2013

Pressure Test: API598

☒ Satisfactory

Shell Pressure:

2225 psi

BackSeat:

1650 psi

Seat Pressure

1650 psi

Seat Air Pressure

80 psi

Chemical Composition [%]													
Spec:	HEAT No	C	Si	Mn	P	S	Ni	Cr	Mo	Cu	V	Nb	Al
Mechanical Properties													
		Transverse Yield	Elong	Redu	Hard	Ch.1	Ch.2	Ch.3	Ch.4	Temp.	HT		
		[ksi]	[ksi]	[%]	[HB]	[f]	[f]	[f]	[f]	[F]			
		[MPa]	[MPa]	[%]	[HV]					[C]			



Inspection Certificate and Material Test Report
(EN10204-1991 3.1.B / EN10204-2004 3.1)

DSI Valve Solutions
12735 Dairy Ashford
Stafford TX 77477
281-637-2000 • Fax 281-637-2299
www.dsi valve.com

Certificate/Serial/Job No:

ZH73 / 9

Quality Department:

John H.

Quantity	Size (NPS)	Class	Product	Description	Type	SONumber	Line	Sold to	Date
6	600		103249	DSI 66LUF-N-LCC	GATE				8/23/2013

Pressure Test:	API598	☒ Satisfactory	Shell Pressure:	2225 psi	BackSeat:	1650 psi	Seal Pressure	1650 psi	Seal Air Pressure	80 psi
				15340.8 kPa		11376 kPa		11376.35 kPa		551.58 kPa

T	Specif.	HEAT No	Chemical Composition [%]														Mechanical Properties									
			C	Si	Mn	P	S	Ni	Cr	Mo	Cu	V	Nb	Al	N	Tensile Yield [ksi] [MPa]	Elong Redu [%]	Hard [HB]	Ch.1 [H]	Ch.2 [H]	Ch.3 [H]	Ch.4 Temp. [F] [C]	HT			
3X	ASTM A352 LCC-2006	2V18106	0.231	0.517	0.827	0.022	0.011	0.334	0.062	0.001	0.029	0.004		0.032		85.55 56.00	30.5	64	180	33	36	31	-50	WT		
																589.85 389.9							-45.56			
NET	ASTM A352 LCC-2006	V218052	0.205	0.491	0.818	0.026	0.013	0.234	0.044	0.001	0.024	0.005		0.041		85.55 589.85	30.5	61	185	28	32	30	-50	WT		
																389.9							-45.56			
DGE	ASTM A352 LCC-2006	E 2141	0.20	0.41	1.07	0.027	0.010	0.20	0.02	0.001	0.014	0.001				85.41 588.88	41.33	31	45	158	32	34	36	-50	WT	
																285							-45.56			

at Treatment Codes:

1: Annealing	AC : Air Cooling	DA : Double Aged	FT : Furnace Treatment	N : Normalizing	OG : Oil Quenched
2: Precipitation Hardening	SA : Solution Annealed	SQ : Solution Quenched	ST : Solution Treatment	T : Tempering	WC : Water Cooling
3: Water Quenched	WT : Water Quenched/Tempered			NT : Normalized/Tempered	

Part	Material	Valves Tested per API598
ACK SEAT	ASTM A276-316	Comply with the requirements of NACE MR0175-2002/MRO103
ODY/BONNET	ASTM A352 LCC	We hereby certify, that the material described above complies with the order requirements.
OLTING	ASTM A320 L7M / ASTM A194 7M	
ISC-WEDGE-CLAPPER	ASTM A352 LCC + 316SS Overlay	
ACKING	GRAPHITE	
EAT RING	ASTM A360-LF2 + Sll.6 Faced	
TEM	ASTM A276-316	
ITEM NUT	ASTM A439-D2	

Declaration of Conformity: JEV (Jiangyin Eastern Valve Co. Ltd.), Jiangsu Province, 214423, P.R. China
According to Annex VII of Pressure Equipment Directive 97/23/EC, hereby declare that the products detailed above are in compliance with PED 97/23/EC and have been manufactured in accordance with the technical specification B+D as approved by the Norwegian Veritas Inspection AB as Identification No 0573 (formally 0409). The products may cover Category I, II and III of pressure equipment. For the most part of this equipment, safety and compliance with essential requirements of the Directive has been based on API 600, API598, ASME B16.34, ASME B16.5, ASME B16.10 latest edition

Undersigned by Liu Jian Qing, representing Jiangyin Eastern Valve Company Ltd.

Signature



Inspection Certificate and Material Test Report (EN10204-1991 3.1.B / EN10204-2004 3.1)

DSI Valve Solutions
12735 Dairy Ashford
Stafford TX 77477
281-637-2000 - Fax 281-637-2299
www.dsi valve.com

Certificate/Serial/Job No:

ZH73 / 9

Quality Department:

John 56

Quantity	Size (NPS)	Class	Product	Description	Type	SONumber	Line	Sold to	Date
6		600		DSI 66LUF-N-LCC	GATE				8/23/2013

Pressure Test: API598 ☒ Satisfactory

Shell Pressure:

2225 psi
15340.8 kPa

BackSeat:

1650 psi
11376 kPa

Seat Pressure

1650 psi
11376.35 kPa

Seal Air Pressure

80 psi
551.58 kPa

Chemical Composition [%]

C	Si	Mn	P	S	Ni	Cr	Mo	Cu	V	Nb	Al	N	Tensile Yield (ksi)	Tensile Yield (MPa)	Elong (%)	Redu (%)	Hard (HBS)	Ch.1 (H)	Ch.2 (H)	Ch.3 (H)	Ch.4 (H)	Temp. (F)	HT (F)

Mechanical Properties



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 38026-220(80150051)

DATE: 2014-4-18

PAGE: 1 OF 4

CUSTOMER

QUANTITY

PART NO.

PRODUCT CODE

PRODUCT DESCRIPTION

NEWAY VALVE INTERNATIONAL INC.-NEWAY
TX 77477 10749 CASH RD. STAFFORD

1

10179018

3GL3RA8-000

GLOBE VALVE 3GL3R C008

[LLC-SSF-MER.]

GLOBE VALVE 3,300LB

ASTM A216 WCB, F6AHF

USA

RAISED FACE END, LOW EMISSION, LOW EMISSION

PURCHASE ORDER:

6001753MRM_S16038009

PRESSURE TEST (Mpa/PSI)

OTHER INSPECTION

PROJECT NAME:

SHELL

HYDROSTATIC

SEATS/BACKSEAT

SEATS

RESULT

OK

VISUAL

OK

DIMENSION

OK

OPERATION

OK

MARKING

OK

7.8/1131

5.7/827

0.6/87

APPLICABLE STANDARDS AND SPECIFICATION:

- PT RATING:

ASME B16.34

- MAIN MATERIAL:

RELEVANT ASTM STANDARD

- DESIGN:

BS1873 ASME B16.34

- TEST:

API598 EN 12265

- TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL

NOTE ALL RELATED STANDARDS ARE THE LATEST VERSION.

WITNESSED BY:

Q.C. Manager

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order.

NEWAY VALVE

Signature

UL1A-DPH-2001
CPO# 42
TF-03400



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC No. 38026-220(80150051)

DATE: 2014.4.18

PAGE: 2 OF 4

PRODUCT TRACEABILITY

[illegible]



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 38026-220(80150051)

DATE: 2014.4.18

PAGE: 3 OF 4

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. C(F)	Holding time(h)	Cooling media	Furnace
F6A-III	NORMALIZE	920-1050(1796-1922F)	1H/25MM 1H	AIR	GAS OR ELECTRIC
F6A-III	TEMPER	595(203F)	1H/25MM 1H	AIR	GAS OR ELECTRIC
We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.					

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS													MECHANICAL PROPERTIES								
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (JOULE)		
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%		HB	TEMP	Avg	Min
			MAX	0.15	1	1	0.03	0.04	13.5	0.5											302			
			MIN						11.5								760	585	15	35	235			
DISC	F6A-III	S2BE008	0.11	0.87	0.78	0.01	0.03	11.9	0.38								768	589	18	39	252			



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 38026-220(80150051)

DATE: 2014.4.18

PAGE: 4 OF 4

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp.C(F)	Holding time(h)	Cooling media	Furnace
WCB	NORMALIZE	93010(170650F)	1H/25MM	AIR	GAS

We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS													MECHANICAL PROPERTIES									
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (J.OULE)			
			%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%			HB	TEMP C	Avg	Min	
		MAX	0.23	1.28	0.6	0.045	0.04	0.5	0.5	0.2	0.3	0.03				655						237			
			MIN															485	250	22	35	135			
BODY	WCB	1H795	0.202	0.98	0.409	0.009	0.033	0.032	0.022	0.009	0.026	0.003				0.377	590	395	26	54	170				
BONNET	WCB	98U87	0.208	0.978	0.412	0.008	0.022	0.043	0.019	0.005	0.018	0.006				0.384	565	390	33	55	156				



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 38026-220(80150051)

DATE: 2014.4.18

PAGE: 1 OF 4

CUSTOMER

QUANTITY

PART NO.

PRODUCT CODE

PRODUCT DESCRIPTION

NEWAY VALVE INTERNATIONAL, INC.-MFM
TX 77477 10749 CASH RD. STAFFORD

1

10179018

3GL3RA8-000

GLOBE VALVE 3GL3R, C00/8

USA

[LIC-SSF-WEB.]
GLOBE VALVE 3.300LB
ASTM A216 WCB F6A/HF
RAISED FACE END LOW EMISSION/LOW EMISSION

PURCHASE ORDER:

6001753MMR_S16038009

PRESSURE TEST (Mpa/PSI)

HYDROSTATIC

PNEUM

RESULT

VISUAL

DIMENSION

OPERATION

MARKING

PROJECT NAME:

SHELL

SEATS/BACKSEAT

SEATS

OK

OK

OK

OK

OK

7.8/1131

5.7/827

0.6/87

APPLICABLE STANDARDS AND SPECIFICATION:

- P/T RATING: ASME B16.34
- MAIN MATERIAL: RELEVANT ASTM STANDARD
- DESIGN: BS1873 ASME B16.34
- TEST: API698 EN12206
- TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL

NOTE: ALL RELATED STANDARDS ARE THE LATEST VERSION.

WITNESSED BY

O.C. Manager

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order

NEWAY VALVE



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC No. 38026-220(80150051)

DATE: 2014.4.18

PAGE: 2 OF 4

PRODUCT TRACEABILITY

[illegible]

MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 38026-220(80150051)

DATE: 2014.4.18


PAGE: 3 OF 4

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp C(F)	Holding time(h)	Cooling media	Furnace
F6A-III	NORMALIZE	930~1050(1796~1922F)	1H/25MM, 1H	AIR	GAS OR ELECTRIC
F6A-III	TEMPER	595(203F)	1H/25MM, 1H	AIR	GAS OR ELECTRIC

We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS													MECHANICAL PROPERTIES									
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (J/CM)			
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%		HB	TEMP	Avg	Min	
			MAX	0.15	1	1	0.03	0.04	13.5	0.5											302				
			MIN						11.5								760	585	15	35	235				
DISC	F6A-III	KCC005	0.14	0.9	0.27	0.024	0.03	11.9	0.46								775	600	22	45	265				
	</																								



EN 10204 2004-3.1

We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.

Address: No. 999 Xinagjiang Road Suzhou New District, China Tel: 86-512-666-51365 Fax: 86-512-666-51360 <http://www.newwayvalve.com>



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 38026-220(80150051)
DATE: 2014-4-18
PAGE: 1 OF 4

CUSTOMER

QUANTITY

PART NO.

PRODUCT CODE

PRODUCT DESCRIPTION

NEWAY VALVE INTERNATIONAL, INC.-MEM.
TX 77477 10749 CASH RD. STAFFORD
USA

1

10179018

3GL3RAB-000

GLOBE VALVE 3GL3R, C0018

[LLC-SF-MEB.1]

GLOBE VALVE 3,300LB

ASTM A216 WCB F5A/HF

RAISED FACE END LOW EMISSION/LOW EMISSION

PURCHASE ORDER:

6001753MRM_S16038009

PRESSURE TEST (Mpa/PSI)

OTHER INSPECTION

PROJECT NAME:

SHELL

SEATS/BACKSEAT

SEATS

OK

OK

OK

OK

OK

7.8/1131

5.7/827

0.6/87

APPLICABLE STANDARDS AND SPECIFICATION:

PT RATING: ASME B16.34

MAIN MATERIAL: RELEVANT ASTM STANDARD

DESIGN: BS1873 ASME B16.34

TEST: API598 EN12265

TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL

NOTE: ALL RELATED STANDARDS ARE THE LATEST VERSION

WITNESSED BY: _____

O.C. Manager

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order:

NEWAY VALVE

O.C. Manager

NEWAY - DPH - 2001
1P02H 92 TF - 03A008



MATERIAL TEST REPORT

EN 10204 2004-3.1


TC No. 38026-220(80150051)

DATE: 2014.4.18

PAGE: 2 OF 4

PRODUCT TRACEABILITY

[illegible]



EN 10204 2004-3.1

PAGE: 4 OF 4

We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.

We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS														MECHANICAL PROPERTIES									
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (J/CM)				
			%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%			HB	TEMP C				
		MAX	0.23	1.28	0.6	0.045	0.04	0.5	0.5	0.2	0.3	0.03				655					237					
			MIN															485	250	22	35	135				
BODY	WCB	2H078	0.2	1.054	0.404	0.009	0.032	0.044	0.024	0.009	0.032	0.004				0.391	550	365	31	49	163					
BONNET	WCB	3H732	0.216	0.959	0.461	0.01	0.019	0.033	0.016	0.005	0.019	0.002				0.386	585	380	32	50	163					



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 38026-220(8015005.1)

DATE: 2014.4.18

PAGE: 3 OF 4

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. C(F)	Holding time(h)	Cooling media	Furnace
F6A-III	NORMALIZE	920-1050(1796-1922F)	1H/25MM 1H	AIR	GAS OR ELECTRIC
F6A-III	TEMPER	595(203F)	1H/25MM 1H	AIR	GAS OR ELECTRIC

We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS														MECHANICAL PROPERTIES							
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (Joule)		
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%		HB	TEMP	Avg	Min
			MAX	0.15	1	1	0.03	0.04	13.5	0.5												302		
			MIN						11.5								760	585	15	35	235			
DISC	F6A-III	S2BE008	0.11	0.87	0.78	0.01	0.03	11.9	0.38								768	589	18	39	252			



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 38026-220(80150051)

DATE: 2014-4-18

PAGE: 1 OF 4

CUSTOMER	QUANTITY	PART NO.	PRODUCT CODE	PRODUCT DESCRIPTION
----------	----------	----------	--------------	---------------------

NEWAY VALVE INTERNATIONAL, INC.-MEXICO TX 77477 10749 CASH RD. STAFFORD USA	1	10179018	3GL3RA8-000	GLOBE VALVE, 3GL3R, C0008 (FLIC-SSF-MEB,1) GLOBE VALVE, 3.300LB ASTM A216 WCB F6A/HF RAISED FACE END, LOW EMISSION, LOW EMISSION
---	---	----------	-------------	--

PURCHASE ORDER:	PRESSURE TEST (Mpa/PSI)			OTHER INSPECTION			
-----------------	-------------------------	--	--	------------------	--	--	--

6001753MRM_S16038009

PROJECT NAME:

HYDROSTATIC		PNEUM	RESULT	VISUAL	DIMENSION	OPERATION	MARKING
SHELL	SEATS/BACKSEAT	SEATS	OK	OK	OK	OK	OK
7.8/1131	5.7/827	0.6/87					

APPLICABLE STANDARDS AND SPECIFICATION:

- P/T RATING: ASME B16.34
- MAIN MATERIAL: RELEVANT ASTM STANDARD
- DESIGN: BS1873 ASME B16.34
- TEST: API598 EN 12266
- TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL

NOTE: ALL RELATED STANDARDS ARE THE LATEST VERSION

NEWAY - DPH - 2001
POST 92 IF - 03A00

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order.

WITNESSED BY:

Q.C. Manager



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC No. 38026-220(80150051)
DATE: 2014.4.18
PAGE: 2 OF 4

PRODUCT TRACEABILITY

[illegible]

FOCUS VENDOR DRAWING REVIEW

☒ A. Approved. Manufacturing may proceed without changes. Submit Carried As Built Drawing

☐ B. Reviewed with comments. Rebuild. Manufacturing may proceed subject to incorporating the changes.

☐ C. Reviewed with comments. Rebuild. Proceed with material order only.

☐ D. Reviewed with comments. Rebuild. DO NOT proceed with manufacturing or material order.

☐ E. Information/Certification-Built

☐ F.

Revisions to proceed after an acceptable inspection of drawing details, and approval, and drawings are submitted by the supplier and then approved by the customer. The customer's approval is required for the drawing to be used for manufacturing.

DATE: 2014.03.20 1 OF 1

REPORT NO : 20140425-010 1 OF 1

DATE : Apr. 25, 2014

ARTICLE : SWINGING BC RF CL150 WCB/13CR(HS)

PIO NO. : 3689

MFG. NO. : 14-00182-008

SIZE : NPS 6

Qty : 1 Pcs.

INSPECTION CERTIFICATE (CHEMICAL, PHYSICAL & HYDROSTATIC)

TAG NO : TNC-3689-008



PK VALVE CO. LTD.
182-1 Shincheon-Dong, Seongnam-Gu
Changwon-city, Korea

Head Office TEL(Int. Phone) : 055 - 268 - 3777

& Factory (O.C Dept) : 055 - 268 - 3788

FAX : 055 - 266 - 2112

Homepage http://www.pkvalve.co.kr

E-mail : als7als7@pkvalve.co.kr

PARTS NAME	ASTM	Body(BD)	Bonnet(BN)	Disc(DS)	Body Seating	Stem
		A216-WCB	A105	A217-CA15	A106-B+STL 6	

DIMENSION INSPECTION (ASME B16.10 & APPROVED DRAWING)									
INSPECTION	Face to Face (End to End)	Flange Diameter	Bolt Circle	Dia. Of Raised Face	Flange Thickness	No. of Bolt Hole	Bolt Hole Diameter	PRESSURE TEST (API 598)	
STANDARD	355.6	279.0	241.3	215.9	25.4	8	22.4	SHELL (PSIG)	SEAT(WATER) (PSIG)
RESULTS	*W.T	W.T	W.T	W.T	W.T	8	W.T	GOOD	GOOD
* W.T : Within Tolerance									

CHEMICAL COMPOSITION (MAX. %) (ASTM STD.)														
HEAT NO.	PARTS	QTY	C	SI	Mn	P	S	NI	Cr	Mo	Cu	V	TS (N/mm ²)	Y.P (N/mm ²)
STANDARD	A216 WCB		0.30	0.60	1.00	0.035	0.035	0.50	0.50	0.20	0.30	0.03	485	250
													665	22.0
STANDARD	A105		0.35	0.10	0.60	0.035	0.035	0.40	0.30	0.12	0.40	0.02	485	250
														22.0
STANDARD	A217 CA15		0.15	1.50	1.00	0.040	0.025	1.00	11.50	0.50			620	450
													795	18.0
72V36	BODY		0.20	0.46	0.77	0.016	0.007	0.08	0.08	0.05	0.04	0.00	525	349
													540	41.1
132721A	BONNET		0.16	0.23	1.14	0.018	0.002	0.06	0.22	0.04	0.09	0.01	540	348
													730	30.0
61AE6	DISC		0.09	0.92	0.62	0.031	0.002	0.18	12.66	0.03			667	29.2
														44.7

BLANK

REMARKS : IN ACCORDANCE WITH EN 10204 TYPE 3.1

HEAT TREATMENT : WCB & CA15 : NORMALIZING 925 C X 2HR(A.C)

HEAT TREATMENT : CA15 : TEMPERING 750 C X 2HR(A.C)

BODY SEATING : WELDING FACED WITH STELLITE 6

C=E+C+Mn6+(Cr+Mo+V)5+(Ni+Cu)15

Genovus FCCL Ltd. c/o DPH Focus

PO#: NL1A-DPH-2000B

Model: 06-152RF8

Line: 8 Tag: CF-01A00

Manager, Q.C Department

Witness Inspector

Signature

We hereby certify that the above items have been tested and inspected in accordance with relevant codes and specifications.

NL1A-2000B
CP#8 CF-01A00

CLIENT DOC NO	NL1A-DPH-2000B-F10-001-05
VENDOR DOC NO	TNC-C008 LINE 8
PROJECT:	12313-A-00
TAG:	NA
Received:	JUNE 02, 2014

FOCUS

NL1A-DPH-2000B-F10-001-05

TNC-C008 LINE 8

12313-A-00

NA

JUNE 02, 2014

PO: NL1A-DPH-2000B

REV: 0

REPORT NO : 20140516-012 1 OF 1

DATE : May 16, 2014

ARTICLE : GATE BB RF CL150 WCB/13CR/FS

P/O NO : 3689

MFG. NO. : 14-00182-011

SIZE : NPS 10

QTY : 2 Pcs.

TAG NO : TNC-3689-011

INSPECTION CERTIFICATE (CHEMICAL, PHYSICAL & HYDROSTATIC)



PK VALVE CO., LTD.
192-1 Shinheui-Dong, Seongnam-City
Changwon, Korea
Head Office TEL: (91) 31-955-3177
& Factory TEL: (91) 31-955-3178
E-MAIL : 3178151@pkvalve.co.kr

PARTS NAME	ASTM	Body(BD)	Bonnet(BN)	Disc(DS)	Body Sealing	Stem
		A216-WCB	A216-WCB	A217-CA15+STL6	A106-B+STL6	A479-410

INSPECTION	Face to Face (End to End)	Flange Diameter	Bolt Circle	Dia. of Raised Face	Flange Thickness	No. of Bolt Hole	Bolt Hole Diameter	SHELL (PSIG)	SEAT(AIR) (PSIG)	BACK SEAT (PSIG)	VISUAL TEST
STANDARD	330.2	406.0	362.0	323.9	30.3	12	25.4	450	80	315	GOOD
RESULTS	W.T	W.T	W.T	W.T	W.T	12	W.T	GOOD	GOOD	GOOD	GOOD

HEAT NO.	PARTS	QTY	CHEMICAL COMPOSITION (MAX. %) (ASTM STD.)												TENSION TEST(MIN.) (ASTM)				HARDNESS	REMARK
			C	Si	Mn	P	S	Ni	Cr	Mo	Cu	V			T.S (N/mm ²)	Y.P (N/mm ²)	EL. %	R.A %	CE	Residual Aluminum
STANDARD	A216 WCB		0.30	0.60	1.00	0.035	0.035	0.50	0.50	0.20	0.30	0.03			485	250	22.0	35.0		MAX 0.45
STANDARD	A217 CA15		0.15	0.15	1.00	0.040	0.025	1.00	11.50 14.00	0.50					620 795	450	18.0	30.0		
72M46	BODY	-	0.18	0.48	0.89	0.013	0.007	0.02	0.02	0.01	0.01	0.00			563	312	32.3	45.9	0.33	0.039
73CJB	BODY	-	0.17	0.42	0.89	0.013	0.007	0.06	0.04	0.01	0.02	0.00			557	315	32.4	48.5	0.33	0.049
71P46	BONNET	-	0.18	0.44	0.81	0.012	0.006	0.02	0.02	0.01	0.02	0.00			564	310	31.7	45.9	0.32	0.040
72N41	BONNET	-	0.18	0.45	0.87	0.012	0.007	0.03	0.03	0.01	0.01	0.00			573	317	32.4	48.3	0.33	0.042
6CFE3	DISC	-	0.09	0.85	0.61	0.021	0.001	0.12	12.45	0.04					720	634	25.0	45.8		
64TE1	DISC	-	0.10	0.91	0.68	0.027	0.002	0.14	12.31	0.05					739	652	29.4	44.8		

REMARKS : IN ACCORDANCE WITH EN 10204 TYPE 3.1

HEAT TREATMENT : WCB & CA15 : NORMALIZING 925°C X 2HR(A/C)
HEAT TREATMENT : CA15 : TEMPERING 750°C X 2HR(A/C)
BODY SEATING & DISC : WELDING FACED WITH STELLITE.6
C-E-C-Mn6+(Cr+Mo+V)/5+(Ni+Cu)/15

Genovus FCC Ltd. c/o DPH Focus
PO#: NL1A-DPH-2000B
Model: 10-G150RF5
Line: 11 Tag: GF-01V00

Manager Q.C Department
Witness Inspector

Signature

We hereby certify that the above items have been tested and inspected in accordance with relevant codes and specifications.

CLIENT DOC NO	NL1A-DPH-2000B-F10-001-15
VENDOR DOC NO	10-G150RF5 (Line 11)
PROJECT	12313A-00
TAG	N/A
REV	0
Received	June 30, 2014

FOCUS

- FOCUS VENDOR DRAWING REVIEW**
- ☒ A. Approved Manufacturing may proceed without changes. Submit Certified As Built Drawing.
 - ☐ B. Reviewed with comments. Resubmit Manufacturing.
 - ☐ C. Reviewed with comments. Resubmit Proceed with material order only.
 - ☐ D. Reviewed with comments. Resubmit DO NOT proceed with manufacturing or material order.
 - ☐ E. Informative Certificate-Only

NL1A-2000B
CPS 211 GF-01V00

DATE: 20140608 BY: [Signature]

Certificate/Serial/Job No:

→ ZF166 / 49

Quality Department:

John 46

Quantity	Size (NPS)	Class	Product	Description	Type	SONumber	Line	Sold to	Date										
50	6	150		103041	DSI 37XUF				8/12/2013										
Pressure Test: API598				☒ Satisfactory	450 psi	BackSeat: 325 psi	Seal Pressure	325 psi	Seal Air Pressure 80 psi										
				Shell Pressure: 3102.64 kPa		2240.8 kPa		2240.8 kPa	551.58 kPa										
Chemical Composition [%]																			
Part	Specif.	HEAT No	C	Si	Mn	P	S	Ni	Cr	Mo	Cu	V	Nb	Al	N	Mechanical Properties			
BODY	ASTM A216 WCB-2008	A 14405	0.21	0.42	0.94	0.027	0.013	0.024	0.064	0.003	0.031	0.006		0.042		Tensile Yield	Elong	Redu	Hard
																ft/lb	ft/lb	%	HB
																MPa	MPa	%	
																505.87	303	54	152
BONNET	ASTM A216 WCB-2008	A 14414	0.20	0.42	0.88	0.024	0.010	0.027	0.054	0.003	0.035	0.008		0.028		74.88	44.37	31	56
																514.90	305.9		153
WEDGE	ASTM A216 WCB-2008	E 3231	0.19	0.44	0.92	0.020	0.006	0.030	0.05	0.010	0.030	0.004				84.97	41.76	32	44
																585.85	287.9		160

Heat Treatment Codes:

A : Annealing	AC : Air Cooling	DA : Double Aged	FT : Furnace Treatment	N : Normalizing	OG : Oil Quenched
Ph-3 : Precipitation Hardening	S4 : Solution Annealed	SQ : Solution Quenched	ST : Solution Treatment	T : Tempering	WC : Water Cooling
HT : Water Quenched	HT : Water Quenched Tempered			NT : Normalized/Tempered	

Part	Material	Valves Tested per API598
BACK SEAT	ASTM A276 410	We hereby certify, that the material described above complies with the order requirements.
BODY/BONNET	ASTM A216 WCB	
BOLTING	ASTM A193 B7 / ASTM A194 2H	
DISC/WEDGE-CLAPPER	ASTM A182 F6A Cr 13	
PACKING	GRAPHITE	
SEAT RING	ASTM A105 + Sll 8 Faced	
STEM	ASTM A182 F6A Cr 13	
STEM NUT	ASTM A439-D2	

EC Declaration of Conformity: JEV (Jiangyin Eastern Valve Co. Ltd.), Jiangsu Province, 214423, P.R. China

According to Annex VII of Pressure Equipment Directive 97/23/EC, hereby declare that the products detailed above are in compliance with PED 97/23/EC and have been manufactured in accordance with conformity assessment module B1D as approved Det Norske Veritas Inspection AB as Identification No 0575 (formerly 0409). The products may cover Category I, II and III of pressure equipment. For the most specific rules of this equipment, safety and compliance with essential requirements of the Directive has been based on API 600, API598, ASME B16.34, ASME B16.5, ASME B16.10 latest edition

Undersigned by: Luo Jian Qun, representing Jiangyin Eastern Valve company Ltd.

Signature

UUA-DPH-2001
PO# 13 6F-01400

Certificate/Serial/Job No:

ZF166 / 49

Quality Department:

John Doe

Quantity	Size (NPS)	Class	Product	Description	Type	SONumber	Line	Sold to	Date
50	6	150		DSI 37XUF	GATE				6/12/2013
Pressure Test: API598 ☒ Satisfactory									
Shell Pressure:				450 psi	BackSeat:	325 psi	Seal Pressure	325 psi	Seal Air Pressure
				3102.64 kPa		2240.8 kPa		2240.8 kPa	80 psi
Pressure Test: 551.58 kPa									

Chemical Composition [%]

Mechanical Properties

Part	Specif.	HEAT No	C	Si	Mn	P	S	Ni	Cr	Mo	Cu	V	Nb	Al	N	Tensile	Yield	Elong	Redu	Hard	Ch.1	Ch.2	Ch.3	Ch.4	Temp.	HT
																psi	psi	%	%	HRB	psi	psi	psi	psi	FT	
																MPa	MPa	%	%	HB	MPa	MPa	MPa	MPa	°C	



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 52147-630(80295430)

DATE: 2014-12-6

PAGE: 1 OF 4

aa line 5 CPO# 116

CUSTOMER

QUANTITY

PART NO.

PRODUCT CODE

PRODUCT DESCRIPTION

NEWAY VALVE INTERNATIONAL, INC-MRM
9757 Stafford Centre Rd., Stafford
USA

1

10178982

2G3RAB-000

GATE VALVE 2G3R, C0018
[LLC-WEBJ]
GATE VALVE 2,300LB
ASTM A216 WCB, F6A/HF
RAISED FACE END, LOW EMISSION

PURCHASE ORDER:

PRESSURE TEST (Mpa/PSI)

OTHER INSPECTION

6003796MRC_S 759 242

PROJECT NAME:

SHELL

SEATS/BACKSEAT

SEATS

OK

OK

OK

OK

OK

7.8/1131

5.7/827

0.6/87

APPLICABLE STANDARDS AND SPECIFICATION:

- P/T RATING: ASME B16.34
- MAIN MATERIAL: RELEVANT ASTM STANDARD
- DESIGN: API600 ASME B16.34
- TEST: API598 EN12266
- TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL

NOTE: ALL RELATED STANDARDS ARE THE LATEST VERSION.

NULIA-DPH-2001
CPO#116 GF-03A10

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order.

NEWAY VALVE

Q.C. Manager

Signature

Time

WITNESSED BY: _____



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC No. 52147-630(80295430)
DATE: 2014.12.6
PAGE: 2 OF 4

PRODUCT TRACEABILITY

[illegible]



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 52147-630(80295430)

DATE: 2014.12.6

PAGE: 3 OF 4

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.																			
CA15	NORMALIZE	1020±10 (1868±50°F)	1H/25MM,≥2H	AIR	GAS FURNACE																				
CA15	TEMPER	670±10 (1238±50°F)	1H/25MM,≥2.5H	AIR	GAS FURNACE																				
PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS													MECHANICAL PROPERTIES									
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (JOULE)			
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%			HB	TEMP °C	Avg	Min
		MAX.	0.15	1	1.5	0.04	0.04	14	1	0.5							795					286			
		MIN.						11.5									620	450	18	30	253				
WEDGE	CA15	74A47	0.1	0.77	0.95	0.01	0.03	12.12	0.1	0.01							693	511	18	44	255				



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 52147-630(80295430)
DATE: 2014.12.6
PAGE: 4 OF 4

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.
WCB	NORMALIZE	920-940 (1688-1724°F)	1H/25MM	AIR	GAS	

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS														MECHANICAL PROPERTIES									
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (Joule)				
			%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%			HB	TEMP °C	Avg	Min		
		MAX.	0.23	1.28	0.6	0.03	0.035	0.5	0.5	0.2	0.3	0.03				655					237					
			MIN.														485	250	22	35	135					
BODY	WCB	873L6	0.19	1.065	0.476	0.013	0.023	0.03	0.019	0.001	0.02	0.007				0.378	530	345	25	53	161					
BONNET	WCB	9318H	0.208	1.092	0.406	0.011	0.023	0.043	0.028	0.004	0.027	0.002				0.403	590	395	29	54	159					



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 52147-580(80308924)
DATE: 2014-12-6
PAGE: 1 OF 4

CUSTOMER	QUANTITY	PART NO.	PRODUCT CODE	PRODUCT DESCRIPTION
----------	----------	----------	--------------	---------------------

NEWAY VALVE INTERNATIONAL, INC-MRM 9757 Stafford Centre Rd., Stafford USA	1	10178963	3G1RA8-000	GATE VALVE 3G1R C00/8 [LLC-WEB,-GBR] GATE VALVE 3,150LB ASTM A216 WCB,F6A/HF RAISED FACE END,LOW EMISSION
---	---	----------	------------	---

PURCHASE ORDER:	PRESSURE TEST (Mpa/PSI)				OTHER INSPECTION			
-----------------	-------------------------	--	--	--	------------------	--	--	--

6003796MRC_S 759 242

PROJECT NAME:	HYDROSTATIC		PNEUM	RESULT	VISUAL	DIMENSION	OPERATION	MARKING
---------------	-------------	--	-------	--------	--------	-----------	-----------	---------

SHELL	SEATS/BACKSEAT	SEATS	OK	OK	OK	OK	OK
3.2/464	2.2/319	0.6/87					

APPLICABLE STANDARDS AND SPECIFICATION:

- P/T RATING: ASME B16.34
- MAIN MATERIAL: RELEVANT ASTM STANDARD
- DESIGN: API600 ASME B16.34
- TEST: API598 EN12286
- TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL

NOTE: ALL RELATED STANDARDS ARE THE LATEST VERSION.

NL1A-DPH+2021
CPO#118 GF-D1A00

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order.

WITNESSED BY: _____
NEWAY VALVE
Q.C. Manager



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC No. 52147-580(80308924)

DATE: 2014.12.6

PAGE: 2 OF 4

PRODUCT TRACEABILITY

[illegible]



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 52147-580(80308924)
DATE: 2014.12.6
PAGE: 3 OF 4

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.
CA15	NORMALIZE	1020±10 (1868±50°F)	1H/25MM,≥2H	AIR	GAS FURNACE	
CA15	TEMPER	670±10 (1238±50°F)	1H/25MM,≥2.5H	AIR	GAS FURNACE	

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS													MECHANICAL PROPERTIES									
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (JOULE)			
			%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%			HB	TEMP °C	Avg	Min	
			MAX.	0.15	1	1.5	0.04	0.04	14	1	0.5					795					286				
			MIN.						11.5							620	450	18	30	253					
WEDGE	CA15	31A18	0.13	0.79	0.96	0.011	0.024	12.59	0.111	0.012						715	504	20	50	256					



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 52147-580(80308924)

DATE: 2014.12.6

PAGE: 4 OF 4

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.																		
WCB	NORMALIZE	920-940 (1688-1724°F)	1H/25MM	AIR	GAS																			
PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS												MECHANICAL PROPERTIES									
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (Joule)		
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%		HB	TEMP °C	Avg	Min
		MAX.	0.23	1.28	0.6	0.03	0.035	0.5	0.5	0.2	0.3	0.03					655				237			
		MIN.															485	250	22	35	135			
BODY	WCB	80L89	0.206	0.972	0.404	0.012	0.03	0.038	0.02	0.001	0.02	0.005				0.379	555	330	31	56	168			
BONNET	WCB	4697L	0.2	1.063	0.424	0.015	0.028	0.051	0.033	0.001	0.019	0.005				0.392	515	320	25	52	156			



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 53001-40(80317191)

DATE: 2014-12-6

PAGE: 1 OF 3

CUSTOMER

NEWAY VALVE INTERNATIONAL, INC.-MRM
9757 Stafford Centre Rd., Stafford
USA
USA

QUANTITY

6

PART NO.

10289143

PRODUCT CODE

3G1RC12-NC-000

PRODUCT DESCRIPTION

GATE VALVE 3G1R.L21/12
[LLC-WEB,-GBR]
GATE VALVE 3.150LB
ASTM A352 LCC,F316/HF
RAISED FACE END,LOW EMISSION

PURCHASE ORDER:

6003945MRC_S 759 248

PRESSURE TEST (Mpa/PSI)

OTHER INSPECTION

PROJECT NAME:

HYDROSTATIC		PNEUM	RESULT	VISUAL	DIMENSION	OPERATION	MARKING
SHELL	SEATS/BACKSEAT	SEATS	OK	OK	OK	OK	OK
3.2/464	2.2/319	0.6/87					

APPLICABLE STANDARDS AND SPECIFICATION:

- PT RATING: ASME B16.34
- MAIN MATERIAL: RELEVANT ASTM STANDARD
- DESIGN: API600 ASME B16.34
- TEST: API598 EN12266
- TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL
- VALVES CONFORM TO NACE STANDARD MR.0175 LATEST REVISION

NOTE: ALL RELATED STANDARDS ARE THE LATEST VERSION.

NL1A-DPH-2001
CPO#120 GF-0/L00

WITNESSED BY: _____

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order.

NEWAY VALVE

Q.C. Manager

Tian-fan



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC No. 53001-40(80317191)
DATE: 2014.12.6
PAGE: 2 OF 3

PRODUCT TRACEABILITY

SERIAL NO.	MATERIAL CODE AND HEAT NO.			SERIAL NO.	MATERIAL CODE AND HEAT NO.			SERIAL NO.	MATERIAL CODE AND HEAT NO.			SERIAL NO.	MATERIAL CODE AND HEAT NO.		
	BODY	BONNET	WEDGE/DISC		BODY	BONNET	WEDGE/DISC		BODY	BONNET	WEDGE/DISC		BODY	BONNET	WEDGE/DISC
53001-040-1	X2880	X1725	6365L	53001-040-2	X2880	X1725	6365L	53001-040-3	X2880	X1725	6365L	53001-040-4	X2880	X1725	6365L
53001-040-5	X2880	X1725	6365L	53001-040-6	X2880	X1725	6365L								



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 53001-40(80317191)
DATE: 2014.12.6
PAGE: 3 OF 3

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace
LCC	NORMALIZE	910-930 (1670-1706°F)	1H/25MM ≥1.5H	AIR	GAS
LCC	QUENCHED	920-940 (1688-1724°F)	1H/25MM ≥2.5H	WATER	GAS
LCC	TEMPER	610-630 (1130-1166°F)	4H	AIR	GAS

We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS										MECHANICAL PROPERTIES										
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (JOULE)	
			%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%		HB	TEMP °C	Avg	Min
		MAX.	0.25	1.2	0.6	0.045	0.04	0.5	0.5	0.2	0.3	0.03				655				237	-50	27.00	22.00
			MIN.														485	275	22	35	135		
WEDGE	LCC	6365L	0.218	1.044	0.399	0.013	0.021	0.025	0.013	0.001	0.022	0.003			0.4	525	355	32	65	159	28	29	32
BONNET	LCC	X1725	0.229	1.088	0.382	0.011	0.02	0.044	0.022	0.004	0.022	0.002			0.423	590	435	31	63	170	58	71	64
BODY	LCC	X2880	0.211	1.081	0.438	0.014	0.026	0.042	0.019	0.005	0.021	0.003			0.404	550	395	33	61	163	50	49	50



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 48082-301(80236402)
DATE: 2014-12-6
PAGE: 1 OF 4

CUSTOMER
NEWAY VALVE INTERNATIONAL, INC
9757 Stafford Centre Rd., Stafford
USA

QUANTITY
1
10178987
8G3RA8-000

PRODUCT CODE
PRODUCT DESCRIPTION
GATE VALVE 8G3R C00/8
[LS-LLC-WEB]
GATE VALVE 8 300LB
ASTM A216 WCB F6A/HF
RAISED FACE END, LOW EMISSION

PURCHASE ORDER:

6003146NVU_CS GCC

PRESSURE TEST (Mpa/Psi)

PROJECT NAME:

HYDROSTATIC

PNEUM

RESULT

VISUAL

DIMENSION

OPERATION

MARKING

SHELL

SEATS/BACKSEAT

SEATS

OK

OK

OK

OK

OK

7.8/1131

5.7/827

0.6/87

APPLICABLE STANDARDS AND SPECIFICATION:

- PT RATING: ASME B16.34
- MAIN MATERIAL: RELEVANT ASTM STANDARD
- DESIGN: API600 ASME B16.34
- TEST: API598 EN12266
- TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL

NOTE: ALL RELATED STANDARDS ARE THE LATEST VERSION.

NL1A-DPIH-2001
CFO#125 GF-03A00

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order.

WITNESSED BY: _____

NEWAY VALVE
Q.C. Manager



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC No. 48082-301(80236402)
DATE: 2014.12.6
PAGE: 2 OF 4

PRODUCT TRACEABILITY

[illegible]



MATERIAL TEST REPORT


EN 10204 2004-3.1

TC NO. 48082-301(80236402)
DATE: 2014.12.6
PAGE: 3 OF 4

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.
CA15	NORMALIZE	1020±10 (1868±50°F)	1H/25MM ≥2H	AIR	GAS FURNACE	
CA15	TEMPER	670±10 (1238±50°F)	1H/25MM ≥2.5H	AIR	GAS FURNACE	

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS													MECHANICAL PROPERTIES						
			C	Mn	Si	S	P	Cr	NI	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (JOULE)
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%		HB	TEMP °C
		MAX.	0.15	1	1.5	0.04	0.04	14	1	0.5							795				286	
		MIN.						11.5									620	450	18	30	253	
WEDGE	CA15	44A15	0.029	0.75	1.07	0.011	0.023	12.63	0.108	0.01							730	522	19	49	255	



We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements

Address: No. 999 Xinagjiang Road Suzhou New District, China Tel: 86-512-666-51365 Fax: 86-512-666-51360 <http://www.newayvalve.com>



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 44132-120(80197665)
DATE: 2014-12-6
PAGE: 1 OF 4

CUSTOMER	QUANTITY	PART NO.	PRODUCT CODE	PRODUCT DESCRIPTION
NEWAY VALVE INTERNATIONAL, INC 9757 Stafford Centre Rd., Stafford USA	1	10178987	8G3RA8-000	GATE VALVE, 8G3R C00/8 [LLC-WEB] GATE VALVE, 8.300LB ASTM A216 WCB, F6A/HF RAISED FACE END, LOW EMISSION

PURCHASE ORDER:	PRESSURE TEST (Mpa/PSI)				OTHER INSPECTION			
	HYDROSTATIC		PNEUM	RESULT	VISUAL	DIMENSION	OPERATION	MARKING
6002624NVU_CSGGC								
PROJECT NAME:	SHELL	SEATS/BACKSEAT	SEATS	OK	OK	OK	OK	OK
	7.8/1131	5.7/827	0.6/87					

APPLICABLE STANDARDS AND SPECIFICATION:

- P/T RATING: ASME B16.34
- MAIN MATERIAL: RELEVANT ASTM STANDARD
- DESIGN: API600 ASME B16.34
- TEST: API598 EN12266
- TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL

NOTE: ALL RELATED STANDARDS ARE THE LATEST VERSION.

NL1A-DPH-2001
CPO#125 GF-03A00

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order.

WITNESSED BY: _____

NEWAY VALVE
Q.C. Manager



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC No. 44132-120(80197665)
DATE: 2014.12.6
PAGE: 2 OF 4

PRODUCT TRACEABILITY

SERIAL NO.	MATERIAL CODE AND HEAT NO.		
	BODY	BONNET	WEDGE/DISC
7L394	WCB	WCB	CA15
76H22	WCB	WCB	CA15
17A40	WCB	WCB	CA15



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 44132-120(80197665)
DATE: 2014.12.6
PAGE: 3 OF 4

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.																			
CA15	NORMALIZE	1020±10 (1868±50°F)	1H/25MM,≥2H	AIR	GAS FURNACE																				
CA15	TEMPER	670±10 (1238±50°F)	1H/25MM,≥2.5H	AIR	GAS FURNACE																				
PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS											MECHANICAL PROPERTIES											
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (J/CM)			
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%			HB	TEMP °C	Avg	Min
			MAX.	0.15	1	1.5	0.04	0.04	14	1	0.5						795					286			
			MIN.						11.5								620	450	18	30	253				
WEDGE	CA15	17A40	0.1	0.78	0.93	0.011	0.025	12.63	0.119	0.011							722	513	20	49	259				



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 44132-120(80197665)
DATE: 2014.12.6
PAGE: 4 OF 4

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.
WCB	NORMALIZE	920~940 (1688~1724°F)	1H/25MM	AIR	GAS	

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS												MECHANICAL PROPERTIES							
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (Joule)
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%		HB	TEMP °C
		MAX.	0.23	1.28	0.6	0.03	0.035	0.5	0.5	0.2	0.3	0.03					655				237	
		MIN.															485	250	22	35	135	
BODY	WCB	7L394	0.206	0.986	0.372	0.017	0.034	0.067	0.039	0.001	0.016	0.004				0.388	515	355	23	54	185	
BONNET	WCB	76H22	0.192	1.09	0.438	0.008	0.028	0.041	0.017	0.011	0.025	0.004				0.388	580	385	35	50	146	



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 50421-1030(80278099)
DATE: 2014-12-6
PAGE: 1 OF 8

CUSTOMER	QUANTITY	PART NO.	PRODUCT CODE	PRODUCT DESCRIPTION
NEWAY VALVE INTERNATIONAL, INC.-MRM 9757 Stafford Centre Rd., Stafford USA USA	7	10460982	10G3RA8-G-000	GATE VALVE, 10G3R-A, C00/8 [BA0C-LLC-O/F35-WEB] GATE VALVE, 10,300LB ASTM A216 WCB, F6A/HF RAISED FACE END, GEAR OPERATED, LOW EMISSION

PURCHASE ORDER:	PRESSURE TEST (Mpa/Psi)				OTHER INSPECTION			
	HYDROSTATIC		PNEUM	RESULT	VISUAL	DIMENSION	OPERATION	MARKING
6003432MRC_S 759 228								
PROJECT NAME:	SHELL	SEATS/BACKSEAT	SEATS	OK	OK	OK	OK	OK
	7.8/1131	5.7/827	0.6/87					

APPLICABLE STANDARDS AND SPECIFICATION:

- P/T RATING: ASME B16.34
- MAIN MATERIAL: RELEVANT ASTM STANDARD
- DESIGN: API600 ASME B16.34
- TEST: API598 EN12266
- TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL

NOTE: ALL RELATED STANDARDS ARE THE LATEST VERSION.

NL1A-DPH-2001
CPO#129 GF-D3A00

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order.

WITNESSED BY: _____

NEWAY VALVE
Q.C. Manager



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC No. 50421-1030(80278099)
DATE: 2014.12.6
PAGE: 2 OF 8

PRODUCT TRACEABILITY

SERIAL NO.	MATERIAL CODE AND HEAT NO.			SERIAL NO.	MATERIAL CODE AND HEAT NO.			SERIAL NO.	MATERIAL CODE AND HEAT NO.			SERIAL NO.	MATERIAL CODE AND HEAT NO.		
	BODY	BONNET	WEDGE/DISC		BODY	BONNET	WEDGE/DISC		BODY	BONNET	WEDGE/DISC		BODY	BONNET	WEDGE/DISC
50421-1030-1	F3854	F3761	51A57	50421-1030-2	F3711	F3825	61A33	50421-1030-3	F3857	F3827	61A33	50421-1030-4	F3855	F3644	61A33
50421-1030-5	F3828	F3761	61A30	50421-1030-6	F3870	F3761	61A33	50421-1030-7	F3872	F3761	61A33				



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 50421-1030(80278099)
DATE: 2014.12.6
PAGE: 3 OF 8

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace
2H	QUENCH		1H/25MM ≥1H	WATER	ELECTRIC
2H	TEMPER		1H/25MM ≥1H	AIR	GAS OR ELECTRIC

We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.

[illegible]



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 50421-1030(80278099)
DATE: 2014.12.6
PAGE: 5 OF 8

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.
B7	QUENCH		1H/25MM≥1H	OIL	ELECTRIC	
B7	TEMPER		1H/25MM≥1H	AIR	GAS OR ELECTRIC	

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS														MECHANICAL PROPERTIES									
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (JOULE)				
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%		HB	TEMP °C	Avg	Min		
			MAX.	0.49	1.1	0.35	0.04	0.035	1.2	0.25											321					
			MIN.	0.37	0.65	0.15			0.75	0.15							860	720	16	50						
BOLT	B7	YCB113	0.42	0.91	0.3	0.004	0.014	1		0.21							934	841	20	61	280					



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 50421-1030(80278099)
DATE: 2014.12.6
PAGE: 6 OF 8

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.
F6A-II	NORMALIZE	980 ~1050 (Nan~1922°F)	1H/25MM,≥1H	AIR	ELECTRIC	
F6A-II	TEMPER	≥675 (≥167°F)	1H/25MM,≥1H	AIR	GAS OR ELECTRIC	

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS													MECHANICAL PROPERTIES									
			C	Mn	SI	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (Joule)			
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%		HB	TEMP °C	Avg	Min	
		MAX.	0.15	1	1	0.03	0.04	13.5	0.5												229				
		MIN.						11.5									585	380	18	35	167				
STEM	F6A-II	TPDCC002	0.098	0.35	0.35	0.008	0.027	12.4	0.17								660	486	28	72	216				



Certificate of Conformance

Certificate #: P4-136702

04 line 3 CPO# 78
Page 1 of 2

Plant 4 Velan Inc.
1010 Cowie Street
Granby, Quebec
Canada, J2J 1E7
Phone : 450-378-2305
Fax : 450-378-6865

Customer Name : MRC CANADA ULC.
Customer Po # : S759225007
Valve Order # : M014-870277-W
Valve Design : API-600
Hydro Test Spec : API-600
Test Result : ACCEPTABLE

NOTES : ALL TESTS AND EXAMINATIONS MEET EN 10204-3.1/ ISO 10474-3.1

IT IS THE END USERS RESPONSIBILITY TO ENSURE THAT MATERIALS ARE SUITABLE FOR THE INTENDED SERVICE.

VALVE(S) MEET(S) NACE MR0175

MATERIAL TEST RESULTS SHOWN BELOW:

CHEMICALS

ASTM Code: A352-06-1CB/LCC-

Heat Code	Dese	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND51D05	BODY	0.191	0.939	0.029	0.010	0.438	0.030	0.281	0.035	0.005	0.007	600.0 / 87.0	375.0 / 54.4	31.4	60.1	/
Heat Treatment	QUEN & TEMP											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
												45.0 / 48.0 / 46.0	-46.0	33.2 / 35.4 / 33.9	-50.8	
Heat Code	Dese	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND51D21	BONNET	0.200	0.950	0.030	0.012	0.414	0.029	0.259	0.043	0.005	0.007	583.0 / 84.6	383.0 / 55.5	29.0	56.0	/
Heat Treatment	QUEN & TEMP											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
												41.0 / 45.0 / 42.0	-46.0	30.2 / 33.2 / 31.0	-50.8	
Heat Code	Dese	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND51F14	BONNET	0.192	0.870	0.027	0.008	0.466	0.033	0.253	0.055	0.010	0.006	587.0 / 85.1	395.0 / 57.3	29.4	57.0	/
Heat Treatment	QUEN & TEMP											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
												40.0 / 43.0 / 46.0	-46.0	29.5 / 31.7 / 33.9	-50.8	
Heat Code	Dese	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND53D07	BODY	0.187	0.852	0.027	0.009	0.484	0.031	0.252	0.034	0.004	0.006	578.0 / 83.8	363.0 / 52.6	32.2	61.1	/
Heat Treatment	QUEN & TEMP											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
												48.0 / 43.0 / 47.0	-46.0	35.4 / 31.7 / 34.7	-50.8	
Heat Code	Dese	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND53F11	BODY	0.191	0.888	0.029	0.012	0.391	0.035	0.262	0.041	0.004	0.008	599.0 / 86.9	399.0 / 57.9	29.0	55.0	/
Heat Treatment	QUEN & TEMP											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
												42.0 / 48.0 / 44.0	-46.0	31.0 / 35.4 / 32.5	-50.8	
Heat Code	Dese	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND54F10	BODY	0.200	0.939	0.031	0.011	0.449	0.037	0.269	0.044	0.004	0.008	546.0 / 79.2	346.0 / 50.2	29.8	57.0	/
Heat Treatment	QUEN & TEMP											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
												40.0 / 44.0 / 45.0	-46.0	29.5 / 32.5 / 33.2	-50.8	

MECHANICALS [F/B: Flattening/ bending; GS: Grain size]

Certificate Date : 02-JAN-2014
Item Number : 13
Quantity : 14
Figure Number : F08-0064C-31NB-W320
Description : VALVE 2" 150 GATE RF
Draw No. & Rev : REV

Tag Number(s) : NONE

NL1A-DPH-2801
CPO# 78 GF-01L200



Velan hereby certifies that the valve(s) described above is (are) in conformance with the purchase order and specification requirements. The test report represents the actual attributes of items furnished and all test results are in full conformance with applicable specification and purchase order requirements.

Date _____

YANCHENG H & M PRESSURE VALVE CO., LTD

NO.6 Juheng Road, Economic Development Zone, Yancheng City, China

Tel: +86-515-8281015

Fax: +86-515-8281015

E-mail: ygf@public.yc.js.cn

Certificate No: KF-1401-04

DATE: 2014.01.13

SHEET 1 OF 1

PRESSURE TEST CERTIFICATE

Pressure Test (As per API 598)						Valve requirement			
Name of Valves: GATE VALVE	Item	Test Pressure (MPa)	Test Durations (Sec.)	Allowable Leakage Rate (max)	Result	Size & Class: 8" 300 LB	Shell Test		
							7.8		
							120		
							0		
							OK		
							Quantity: 2		
Backseat Test	5.8	60	0	OK	Valve Material: ASTM A216 WCB				
Hydro	5.8	120	0	OK	PO No.: P31255				
Test	0.6	120	0	OK	CAT No.: GA03011XU-8"-GO	Test	Air		
API600 (✓) BS1873 () BS1868 ()								NACE MR 0175 ()	

Serial No.		Heat No.		Body	Bonnet	Wedge	Seat Ring	Stem	Back Seat	Bolt	Nut
KF813110005	A60711	A60624	A60620	A13067	S13082	T41012	...	...	...	...	...
KF813110006	A60620	A60620	A60612	A13067	S13082	T41012	...	...	...	...	...

YANCHENG H & M PRESSURE VALVE CO., LTD

NO.6 Juheng Road, Economic Development Zone, Yancheng City, China

Certificate No: KF-1401-03


DATE: 2014.01.10

SHEET 1 OF 1

PRESSURE TEST CERTIFICATE

Pressure Test (As per API 598)		Name of Valves: GATE VALVE	
Item	Test Pressure (MPa)	Test Durations (Sec.)	Allowable Leakage Rate (max)
Shell Test Backseat Test Hydro Test	3.2	120	0
	2.2	60	0
	2.2	120	0
	0.6	120	0
	Air		
Valve requirement		AP1600 (✓) BS1873 () BS1868 ()	
NACE MR 0175 ()			

[illegible]

YANCHENG H & M PRESSURE VALVE CO., LTD										MATERIAL CERTIFICATE										Certificate No: KF-1401-03					
No.6 Juheng Road Economic development Zone Yancheng City, China										(BS EN 10204.3.1)										Certificate Date: 2014/01/10					
Tel: +86-515-8281015 Fax: +86-515-8281003										Customer: KF										P/O No: P31240		QTY: 3		Material: ASTM A216 WCB	
E-mail: yqf@public.yc.js.cn										Description: GATE VALVE 12" 150LB										CAT No: GA01011XU-12"-GO		Sheet 1 of 2			
Name of Parts	Heat No.	CHEMICAL ANALYSIS (%) MAX												MECHANICAL PROPERTIES											
		C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	Others	Tensile 485-655 Mpa	Yield 250Min. MPa	Elongation 22% Min.	Reduction 35% Min.	Hardness HB								
BODY	A60632	0.194	0.680	0.029	0.022	0.430	0.043	0.055	0.199	0.037	0.009		509	271	30	40	172								
BODY	A60634	0.218	0.660	0.025	0.014	0.390	0.035	0.040	0.083	0.017	0.006		517	259	23	38	171								
BONNET	A60632	0.194	0.680	0.029	0.022	0.430	0.043	0.055	0.199	0.037	0.009		509	271	30	40	172								
WEDGE	A60442	0.208	0.720	0.028	0.019	0.455	0.027	0.036	0.059	0.020	0.001		500	269	26	39	169								
WEDGE	A60407	0.210	0.740	0.030	0.020	0.420	0.025	0.032	0.061	0.023	0.002		507	266	28	37	174								
WEDGE	A69227	0.207	0.740	0.027	0.014	0.440	0.010	0.036	0.039	0.023	0.001		500	260	25	38	161								
HEAT TREATMENT		REMARKS															Signature / Date		Inspector						
Normalizing		We hereby certify that the materials described above have been tested and comply to the material specifications of the purchase order.																							

Plant: 4 Velan Inc.
1810 Cowie Street
Granby, Quebec
Canada, J1A 1E7
Phone: 450-378-2205
Fax: 450-378-6865

Customer Name: MHC CANADA ULC.
Customer Po #: 578421M42
Design Spec: API 600
Drawing Number: N/A
Tag Number(s): NONE

Velan Order #: M014-869727-W
Item Number: 03 Position No: 15
Quantity: 42
Figure Number: F14-0064C-02TY-WJ20
Description: VALVE 6" 150 GATE RF

NOTES: REF. CERT # 133342

Test Standard: API 598

Dimensional Examination: ACCEPTABLE

Markings MSS SP-25: ACCEPTABLE

Visual: ACCEPTABLE

Test Type	Steel	Forging	Steel (H.C.)	Steel (L.E.)	Bridgman
Duration (Sec)	60	60	N/A	60	60
Pressure (Psi)	450	450	N/A	80	325
Result	ACCEPTABLE	ACCEPTABLE	N/A	ACCEPTABLE	ACCEPTABLE

MATERIAL TEST RESULTS SHOWN BELOW:

CHEMICALS

Supplier: BN
Heat Code: BND01C2B
ASTM Code: A216-08-WCB
Description: BUDY

Carbon (C)	0.189	Manganese (Mn)	0.916	Phosphorus (P)	0.025
Sulfur (S)	0.009	Silicon (Si)	0.458	Copper (Cu)	0.034
Nickel (Ni)	0.035	Chromium (Cr)	0.042	Molybdenum (Mo)	0.005
Vanadium (V)	0.007				
C.E.	0.357				

MECHANICALS

Tensile (ksi)	583,000	Tensile (ksi)	84,557
Yield (ksi)	379,000	Yield (ksi)	54,989
Elongation (%)	31.810	Reduction of Area (%)	54.900
Heat Treatment	NORMALIZED		

Supplier: BN
Heat Code: BND02C2A
ASTM Code: A216-08-WCB
Description: BUDY

Carbon (C)	0.191	Manganese (Mn)	0.957	Phosphorus (P)	0.025
Sulfur (S)	0.006	Silicon (Si)	0.424	Copper (Cu)	0.030
Nickel (Ni)	0.027	Chromium (Cr)	0.041	Molybdenum (Mo)	0.005
Vanadium (V)	0.007				
C.E.	0.365				

Tensile (ksi)	591,000	Tensile (ksi)	85,717
Yield (ksi)	395,000	Yield (ksi)	57,290
Elongation (%)	29.000	Reduction of Area (%)	55.000
Heat Treatment	NORMALIZED		

VELLA - DPH - 2001
CPO#49 GF-01A00

OK Line 21 CPO#49 ①

CHEMICALS

MECHANICALS

Supplier: BN	Carbon (C)	0.191	Manganese (Mn)	0.941	Phosphorus (P)	0.033	Tensile (MPa)	563,000	Tensile (ksi)	81,656
Heat Code: BND02C16	Sulfur (S)	0.010	Silicon (Si)	0.469	Copper (Cu)	0.035	Yield (MPa)	355,000	Yield (ksi)	51,488
ASTM Code: A216-08-WCB	Nickel (Ni)	0.031	Chromium (Cr)	0.041	Molybdenum (Mo)	0.006	Elongation (%)	29,400	Reduction Of Area (%)	53,000
Description: BODY	Vanadium (V)	0.008					Heat Treatment	NORMALIZED		
	C.E.	0.363								

Supplier: BN	Carbon (C)	0.194	Manganese (Mn)	0.947	Phosphorus (P)	0.030	Tensile (MPa)	537,000	Tensile (ksi)	77,385
Heat Code: BND02D09	Sulfur (S)	0.011	Silicon (Si)	0.472	Copper (Cu)	0.033	Yield (MPa)	338,000	Yield (ksi)	49,023
ASTM Code: A216-08-WCB	Nickel (Ni)	0.045	Chromium (Cr)	0.035	Molybdenum (Mo)	0.005	Elongation (%)	33,800	Reduction Of Area (%)	62,100
Description: BODY	Vanadium (V)	0.008					Heat Treatment	NORMALIZED		
	C.E.	0.350								

Supplier: BN	Carbon (C)	0.200	Manganese (Mn)	0.987	Phosphorus (P)	0.026	Tensile (MPa)	565,000	Tensile (ksi)	81,946
Heat Code: BND02D11	Sulfur (S)	0.009	Silicon (Si)	0.413	Copper (Cu)	0.029	Yield (MPa)	306,000	Yield (ksi)	44,382
ASTM Code: A216-08-WCB	Nickel (Ni)	0.022	Chromium (Cr)	0.035	Molybdenum (Mo)	0.004	Elongation (%)	31,000	Reduction Of Area (%)	53,900
Description: BODY	Vanadium (V)	0.006					Heat Treatment	NORMALIZED		
	C.E.	0.377								

Supplier: BN	Carbon (C)	0.187	Manganese (Mn)	0.971	Phosphorus (P)	0.022	Tensile (MPa)	561,000	Tensile (ksi)	81,366
Heat Code: BND01C24	Sulfur (S)	0.006	Silicon (Si)	0.401	Copper (Cu)	0.037	Yield (MPa)	565,000	Yield (ksi)	56,275
ASTM Code: A216-08-WCB	Nickel (Ni)	0.076	Chromium (Cr)	0.047	Molybdenum (Mo)	0.006	Elongation (%)	31,600	Reduction Of Area (%)	61,100
Description: BODY	Vanadium (V)	0.006					Heat Treatment	NORMALIZED		
	C.E.	0.368								

Supplier: BN	Carbon (C)	0.186	Manganese (Mn)	0.895	Phosphorus (P)	0.033	Tensile (MPa)	599,000	Tensile (ksi)	86,878
Heat Code: BND01C26	Sulfur (S)	0.012	Silicon (Si)	0.435	Copper (Cu)	0.049	Yield (MPa)	383,000	Yield (ksi)	55,549
ASTM Code: A216-08-WCB	Nickel (Ni)	0.056	Chromium (Cr)	0.057	Molybdenum (Mo)	0.009	Elongation (%)	33,400	Reduction Of Area (%)	58,000
Description: BODY	Vanadium (V)	0.011					Heat Treatment	NORMALIZED		
	C.E.	0.358								

CHEMICALS

MECHANICALS

Supplier: BN	Carbon (C)	0.140	Manganese (Mn)	0.066	Phosphorous (P)	0.032	Tensile (MPa)	548,000	Tensile (ksi)	79,481
Heat Code: BND00J011	Sulfur (S)	0.010	Silicon (Si)	0.463	Copper (Cu)	0.030	Yield (MPa)	363,000	Yield (ksi)	52,049
ASTM Code: A216-08-WCB	Nickel (Ni)	0.028	Chromium (Cr)	0.042	Molybdenum (Mo)	0.005	Elongation (%)	36,400	Reduction Of Area (%)	62,100
Description: BONNET	Vanadium (V)	0.010					Heat Treatment	NORMALIZED		
	C.E.	0.350								

Supplier: BN	Carbon (C)	0.150	Manganese (Mn)	0.047	Phosphorous (P)	0.035	Tensile (MPa)	563,000	Tensile (ksi)	81,636
Heat Code: BND04C24	Sulfur (S)	0.008	Silicon (Si)	0.437	Copper (Cu)	0.033	Yield (MPa)	363,000	Yield (ksi)	52,049
ASTM Code: A216-08-WCB	Nickel (Ni)	0.031	Chromium (Cr)	0.054	Molybdenum (Mo)	0.021	Elongation (%)	30,400	Reduction Of Area (%)	58,000
Description: BODY	Vanadium (V)	0.009					Heat Treatment	NORMALIZED		
	C.E.	0.348								

Supplier: BN	Carbon (C)	0.192	Manganese (Mn)	0.925	Phosphorous (P)	0.033	Tensile (MPa)	503,000	Tensile (ksi)	81,636
Heat Code: BND04C28	Sulfur (S)	0.011	Silicon (Si)	0.421	Copper (Cu)	0.040	Yield (MPa)	351,000	Yield (ksi)	50,908
ASTM Code: A216-08-WCB	Nickel (Ni)	0.037	Chromium (Cr)	0.048	Molybdenum (Mo)	0.004	Elongation (%)	29,400	Reduction Of Area (%)	57,000
Description: BODY	Vanadium (V)	0.009					Heat Treatment	NORMALIZED		
	C.E.	0.364								

Supplier: BN	Carbon (C)	0.189	Manganese (Mn)	0.903	Phosphorous (P)	0.029	Tensile (MPa)	559,000	Tensile (ksi)	81,076
Heat Code: BND06C28	Sulfur (S)	0.013	Silicon (Si)	0.457	Copper (Cu)	0.004	Yield (MPa)	371,000	Yield (ksi)	53,509
ASTM Code: A216-08-WCB	Nickel (Ni)	0.041	Chromium (Cr)	0.049	Molybdenum (Mo)	0.006	Elongation (%)	36,000	Reduction Of Area (%)	59,100
Description: BONNET	Vanadium (V)	0.006					Heat Treatment	NORMALIZED		
	C.E.	0.355								

Supplier: BN	Carbon (C)	0.200	Manganese (Mn)	0.911	Phosphorous (P)	0.029	Tensile (MPa)	557,000	Tensile (ksi)	80,412
Heat Code: BND07D15	Sulfur (S)	0.016	Silicon (Si)	0.417	Copper (Cu)	0.041	Yield (MPa)	379,000	Yield (ksi)	54,909
ASTM Code: A216-08-WCB	Nickel (Ni)	0.033	Chromium (Cr)	0.040	Molybdenum (Mo)	0.005	Elongation (%)	33,200	Reduction Of Area (%)	57,000
Description: BODY	Vanadium (V)	0.008					Heat Treatment	NORMALIZED		
	C.E.	0.367								

CHEMICALS

MECHANICALS

Supplier: BN	Carbon (C)	0.190	Manganese (Mn)	0.046	Phosphorus (P)	0.032	Tensile (MPa)	581,000	Tensile (ksi)	84,267
Heat Code: BND080D12	Sulfur (S)	0.008	Silicon (Si)	0.396	Copper (Cu)	0.031	Yield (MPa)	387,000	Yield (ksi)	55,130
ASTM Code: A216-08-WCB	Nickel (Ni)	0.004	Chromium (Cr)	0.059	Molybdenum (Mo)	0.004	Elongation (%)	29.800	Reduction Of Area (%)	58.800
Description: BODY	Vanadium (V)	0.007					Heat Treatment	NORMALIZED		
	C.E.	0.369								

Supplier: BN	Carbon (C)	0.195	Manganese (Mn)	0.090	Phosphorus (P)	0.031	Tensile (MPa)	583,000	Tensile (ksi)	84,557
Heat Code: BND080D15	Sulfur (S)	0.010	Silicon (Si)	0.435	Copper (Cu)	0.038	Yield (MPa)	375,000	Yield (ksi)	54,389
ASTM Code: A216-08-WCB	Nickel (Ni)	0.042	Chromium (Cr)	0.054	Molybdenum (Mo)	0.008	Elongation (%)	32.200	Reduction Of Area (%)	62.100
Description: BODY	Vanadium (V)	0.009					Heat Treatment	NORMALIZED		
	C.E.	0.378								

Supplier: BN	Carbon (C)	0.192	Manganese (Mn)	0.022	Phosphorus (P)	0.031	Tensile (MPa)	570,000	Tensile (ksi)	82,671
Heat Code: BND10D12	Sulfur (S)	0.015	Silicon (Si)	0.436	Copper (Cu)	0.038	Yield (MPa)	371,000	Yield (ksi)	53,809
ASTM Code: A216-08-WCB	Nickel (Ni)	0.035	Chromium (Cr)	0.053	Molybdenum (Mo)	0.004	Elongation (%)	35.400	Reduction Of Area (%)	59.100
Description: BODY	Vanadium (V)	0.008					Heat Treatment	NORMALIZED		
	C.E.	0.364								

Supplier: BN	Carbon (C)	0.187	Manganese (Mn)	0.068	Phosphorus (P)	0.034	Tensile (MPa)	573,000	Tensile (ksi)	83,397
Heat Code: BND11D08	Sulfur (S)	0.009	Silicon (Si)	0.498	Copper (Cu)	0.032	Yield (MPa)	379,000	Yield (ksi)	54,969
ASTM Code: A216-08-WCB	Nickel (Ni)	0.051	Chromium (Cr)	0.072	Molybdenum (Mo)	0.010	Elongation (%)	31.600	Reduction Of Area (%)	57.000
Description: BONNET	Vanadium (V)	0.009					Heat Treatment	NORMALIZED		
	C.E.	0.355								

Supplier: BN	Carbon (C)	0.188	Manganese (Mn)	0.026	Phosphorus (P)	0.023	Tensile (MPa)	572,000	Tensile (ksi)	82,962
Heat Code: BND13C29	Sulfur (S)	0.007	Silicon (Si)	0.397	Copper (Cu)	0.026	Yield (MPa)	379,000	Yield (ksi)	54,969
ASTM Code: A216-08-WCB	Nickel (Ni)	0.054	Chromium (Cr)	0.039	Molybdenum (Mo)	0.003	Elongation (%)	34.000	Reduction Of Area (%)	59.100
Description: BONNET	Vanadium (V)	0.006					Heat Treatment	NORMALIZED		
	C.E.	0.357								

CHEMICALS

Supplier:	BN	Carbon (C)	0.187	Manganese (Mn)	0.063	Phosphorus (P)	0.028	Tensile (MPa)	564.000	Tensile (ksi)	81.801
Heat Code:	BND13129	Sulfur (S)	0.006	Silicon (Si)	0.466	Copper (Cu)	0.045	Yield (MPa)	367.000	Yield (ksi)	53.229
ASTM Code:	A216-08-WCB	Nickel (Ni)	0.061	Chromium (Cr)	0.082	Molybdenum (Mo)	0.021	Elongation (%)	36.000	Reduction Of Area (%)	62.100
Description:	BONNET	Vanadium (V)	0.012					Heat Treatment	NORMALIZED		
		C.E.	0.378								

MECHANICALS

Supplier:	BN	Carbon (C)	0.210	Manganese (Mn)	0.090	Phosphorus (P)	0.031	Tensile (MPa)	383.000	Tensile (ksi)	55.557
Heat Code:	BND14C29	Sulfur (S)	0.009	Silicon (Si)	0.439	Copper (Cu)	0.034	Yield (MPa)	383.000	Yield (ksi)	55.549
ASTM Code:	A216-08-WCB	Nickel (Ni)	0.036	Chromium (Cr)	0.032	Molybdenum (Mo)	0.007	Elongation (%)	32.000	Reduction Of Area (%)	59.100
Description:	BONNET	Vanadium (V)	0.009					Heat Treatment	NORMALIZED		
		C.E.	0.368								

Supplier:	BN	Carbon (C)	0.195	Manganese (Mn)	0.041	Phosphorus (P)	0.029	Tensile (MPa)	566.000	Tensile (ksi)	82.091
Heat Code:	BND16D16	Sulfur (S)	0.010	Silicon (Si)	0.419	Copper (Cu)	0.026	Yield (MPa)	555.000	Yield (ksi)	80.488
ASTM Code:	A216-08-WCB	Nickel (Ni)	0.024	Chromium (Cr)	0.012	Molybdenum (Mo)	0.005	Elongation (%)	32.200	Reduction Of Area (%)	58.000
Description:	BOUY	Vanadium (V)	0.007					Heat Treatment	NORMALIZED		
		C.E.	0.347								

Supplier:	BN	Carbon (C)	0.198	Manganese (Mn)	0.037	Phosphorus (P)	0.033	Tensile (MPa)	535.000	Tensile (ksi)	77.595
Heat Code:	BND20D12	Sulfur (S)	0.009	Silicon (Si)	0.435	Copper (Cu)	0.030	Yield (MPa)	390.000	Yield (ksi)	56.761
ASTM Code:	A216-08-WCB	Nickel (Ni)	0.041	Chromium (Cr)	0.041	Molybdenum (Mo)	0.004	Elongation (%)	32.800	Reduction Of Area (%)	60.100
Description:	BOUY	Vanadium (V)	0.007					Heat Treatment	NORMALIZED		
		C.E.	0.369								

Supplier:	BN	Carbon (C)	0.193	Manganese (Mn)	0.036	Phosphorus (P)	0.031	Tensile (MPa)	565.000	Tensile (ksi)	81.946
Heat Code:	BND21D13	Sulfur (S)	0.009	Silicon (Si)	0.481	Copper (Cu)	0.040	Yield (MPa)	363.000	Yield (ksi)	52.549
ASTM Code:	A216-08-WCB	Nickel (Ni)	0.042	Chromium (Cr)	0.056	Molybdenum (Mo)	0.010	Elongation (%)	33.000	Reduction Of Area (%)	54.900
Description:	BONNET	Vanadium (V)	0.010					Heat Treatment	NORMALIZED		
		C.E.	0.370								

CHEMICALS

MECHANICALS

Supplier: BN	Carbon (C)	0.19	Manganese (Mn)	0.446	Phosphorus (P)	0.022	Tensile (ksi)	79.916
Heat Code: BND210B9	Sulfur (S)	0.008	Silicon (Si)	0.480	Copper (Cu)	0.029	Yield (ksi)	52.649
ASTM Code: A216-08-WCB	Nickel (Ni)	0.022	Chromium (Cr)	0.039	Molybdenum (Mo)	0.006	Elongation (%)	34.000
Description: BODY	Vanadium (V)	0.006					Reduction Of Area (%)	57.000
	C.E.	0.345					Heat Treatment	NORMALIZED

Supplier: BN	Carbon (C)	0.186	Manganese (Mn)	0.926	Phosphorus (P)	0.029	Tensile (ksi)	82.091
Heat Code: BND24CJ1	Sulfur (S)	0.009	Silicon (Si)	0.435	Copper (Cu)	0.029	Yield (ksi)	52.649
ASTM Code: A216-08-WCB	Nickel (Ni)	0.028	Chromium (Cr)	0.039	Molybdenum (Mo)	0.006	Elongation (%)	31.600
Description: BODY	Vanadium (V)	0.007					Reduction Of Area (%)	58.000
	C.E.	0.355					Heat Treatment	NORMALIZED

Supplier: BN	Carbon (C)	0.200	Manganese (Mn)	0.945	Phosphorus (P)	0.029	Tensile (ksi)	81.511
Heat Code: BND24D24	Sulfur (S)	0.010	Silicon (Si)	0.434	Copper (Cu)	0.028	Yield (ksi)	53.379
ASTM Code: A216-08-WCB	Nickel (Ni)	0.049	Chromium (Cr)	0.038	Molybdenum (Mo)	0.004	Elongation (%)	31.600
Description: BODY	Vanadium (V)	0.013					Reduction Of Area (%)	58.000
	C.E.	0.374					Heat Treatment	NORMALIZED

Supplier: BN	Carbon (C)	0.200	Manganese (Mn)	0.958	Phosphorus (P)	0.031	Tensile (ksi)	86.538
Heat Code: BND25C25	Sulfur (S)	0.011	Silicon (Si)	0.438	Copper (Cu)	0.045	Yield (ksi)	56.130
ASTM Code: A216-08-WCB	Nickel (Ni)	0.052	Chromium (Cr)	0.051	Molybdenum (Mo)	0.007	Elongation (%)	35.000
Description: BODY	Vanadium (V)	0.008					Reduction Of Area (%)	58.000
	C.E.	0.379					Heat Treatment	NORMALIZED

Supplier: BN	Carbon (C)	0.194	Manganese (Mn)	0.910	Phosphorus (P)	0.029	Tensile (ksi)	85.862
Heat Code: BND25D19	Sulfur (S)	0.009	Silicon (Si)	0.457	Copper (Cu)	0.020	Yield (ksi)	59.763
ASTM Code: A216-08-WCB	Nickel (Ni)	0.033	Chromium (Cr)	0.052	Molybdenum (Mo)	0.005	Elongation (%)	37.000
Description: BODY	Vanadium (V)	0.007					Reduction Of Area (%)	57.000
	C.E.	0.363					Heat Treatment	NORMALIZED

CHEMICALS

MECHANICALS

Supplier: BN	Carbon (C)	0.185	Manganese (Mn)	0.920	Phosphorus (P)	0.025	Tensile (MPa)	570,000	Tensile (ksi)	82.671
Heat Code: BND27C16	Sulfur (S)	0.010	Silicon (Si)	0.392	Copper (Cu)	0.029	Yield (MPa)	371,000	Yield (ksi)	53.809
ASTM Code: A216-08-WCB-	Nickel (Ni)	0.028	Chromium (Cr)	0.035	Molybdenum (Mo)	0.004	Elongation (%)	33.200	Reduction Of Area (%)	38.000
Description: BODY	Vanadium (V)	0.006					Heat Treatment	NORMALIZED		
	C.E.	0.357								

Supplier: BN	Carbon (C)	0.201	Manganese (Mn)	0.912	Phosphorus (P)	0.027	Tensile (MPa)	550,000	Tensile (ksi)	79.771
Heat Code: BND27C30	Sulfur (S)	0.007	Silicon (Si)	0.406	Copper (Cu)	0.030	Yield (MPa)	359,000	Yield (ksi)	52.069
ASTM Code: A216-08-WCB-	Nickel (Ni)	0.024	Chromium (Cr)	0.062	Molybdenum (Mo)	0.010	Elongation (%)	31.100	Reduction Of Area (%)	55.900
Description: BODY	Vanadium (V)	0.009					Heat Treatment	NORMALIZED		
	C.E.	0.373								

Supplier: BN	Carbon (C)	0.200	Manganese (Mn)	0.939	Phosphorus (P)	0.032	Tensile (MPa)	530,000	Tensile (ksi)	76.570
Heat Code: BND28D03	Sulfur (S)	0.013	Silicon (Si)	0.444	Copper (Cu)	0.033	Yield (MPa)	359,000	Yield (ksi)	52.069
ASTM Code: A216-08-WCB-	Nickel (Ni)	0.031	Chromium (Cr)	0.043	Molybdenum (Mo)	0.005	Elongation (%)	31.200	Reduction Of Area (%)	54.000
Description: BODY	Vanadium (V)	0.008					Heat Treatment	NORMALIZED		
	C.E.	0.372								

Supplier: BN	Carbon (C)	0.201	Manganese (Mn)	0.978	Phosphorus (P)	0.026	Tensile (MPa)	566,000	Tensile (ksi)	82.091
Heat Code: BND29D05	Sulfur (S)	0.009	Silicon (Si)	0.354	Copper (Cu)	0.030	Yield (MPa)	363,000	Yield (ksi)	52.649
ASTM Code: A216-08-WCB-	Nickel (Ni)	0.020	Chromium (Cr)	0.032	Molybdenum (Mo)	0.004	Elongation (%)	36.400	Reduction Of Area (%)	57.000
Description: BODY	Vanadium (V)	0.007					Heat Treatment	NORMALIZED		
	C.E.	0.376								

Supplier: BN	Carbon (C)	0.189	Manganese (Mn)	0.941	Phosphorus (P)	0.029	Tensile (MPa)	565,000	Tensile (ksi)	81.946
Heat Code: BND30H04	Sulfur (S)	0.008	Silicon (Si)	0.462	Copper (Cu)	0.032	Yield (MPa)	359,000	Yield (ksi)	52.069
ASTM Code: A216-08-WCB-	Nickel (Ni)	0.035	Chromium (Cr)	0.038	Molybdenum (Mo)	0.005	Elongation (%)	31.400	Reduction Of Area (%)	62.000
Description: BODY	Vanadium (V)	0.007					Heat Treatment	NORMALIZED		
	C.E.	0.360								

CHEMICALS

Supplier: BN
Heat Code: BND31CB8
ASTM Code: A216-08-WCB-
Description: BONNET

Carbon (C)	0.280	Manganese (Mn)	0.336	Phosphorus (P)	0.028
Sulfur (S)	0.013	Silicon (Si)	0.490	Copper (Cu)	0.035
Nickel (Ni)	0.031	Chromium (Cr)	0.066	Molybdenum (Mo)	0.004
Vanadium (V)	0.008				
C.E.	0.372				

MECHANICALS

Tensile (MPa)	591,000	Tensile (ksi)	85,572
Yield (MPa)	391,000	Yield (ksi)	56,710
Elongation (%)	31,400	Reduction Of Area (%)	58,000
Heat Treatment	NORMALIZED		

Supplier: BN
Heat Code: BND31CB8
ASTM Code: A216-08-WCB-
Description: BONNET

Carbon (C)	0.187	Manganese (Mn)	0.911	Phosphorus (P)	0.027
Sulfur (S)	0.008	Silicon (Si)	0.450	Copper (Cu)	0.032
Nickel (Ni)	0.029	Chromium (Cr)	0.039	Molybdenum (Mo)	0.005
Vanadium (V)	0.007				
C.E.	0.353				

Tensile (MPa)	551,000	Tensile (ksi)	79,916
Yield (MPa)	399,000	Yield (ksi)	52,069
Elongation (%)	31,600	Reduction Of Area (%)	61,100
Heat Treatment	NORMALIZED		

Supplier: BN
Heat Code: BND31B02
ASTM Code: A216-08-WCB-
Description: BODY

Carbon (C)	0.186	Manganese (Mn)	0.907	Phosphorus (P)	0.026
Sulfur (S)	0.008	Silicon (Si)	0.475	Copper (Cu)	0.034
Nickel (Ni)	0.033	Chromium (Cr)	0.039	Molybdenum (Mo)	0.005
Vanadium (V)	0.007				
C.E.	0.352				

Tensile (MPa)	560,000	Tensile (ksi)	81,231
Yield (MPa)	367,000	Yield (ksi)	53,229
Elongation (%)	31,600	Reduction Of Area (%)	60,100
Heat Treatment	NORMALIZED		

Supplier: BN
Heat Code: BND31B04
ASTM Code: A216-08-WCB-
Description: BODY

Carbon (C)	0.201	Manganese (Mn)	0.900	Phosphorus (P)	0.028
Sulfur (S)	0.013	Silicon (Si)	0.462	Copper (Cu)	0.029
Nickel (Ni)	0.023	Chromium (Cr)	0.041	Molybdenum (Mo)	0.004
Vanadium (V)	0.007				
C.E.	0.365				

Tensile (MPa)	553,000	Tensile (ksi)	80,306
Yield (MPa)	346,000	Yield (ksi)	50,183
Elongation (%)	32,000	Reduction Of Area (%)	60,100
Heat Treatment	NORMALIZED		

Supplier: BN
Heat Code: BND31B06
ASTM Code: A216-08-WCB-
Description: BODY

Carbon (C)	0.202	Manganese (Mn)	0.958	Phosphorus (P)	0.031
Sulfur (S)	0.011	Silicon (Si)	0.477	Copper (Cu)	0.035
Nickel (Ni)	0.027	Chromium (Cr)	0.037	Molybdenum (Mo)	0.005
Vanadium (V)	0.007				
C.E.	0.376				

Tensile (MPa)	571,000	Tensile (ksi)	83,107
Yield (MPa)	367,000	Yield (ksi)	56,130
Elongation (%)	15,000	Reduction Of Area (%)	62,100
Heat Treatment	NORMALIZED		

INSPECTION CERTIFICATE
EN-10204-3.1

Page 4 of 11

Certificate #: 74756

CHEMICALS

Supplier:	BN	Carbon (C)	0.195	Manganese (Mn)	0.447	Phosphorus (P)	0.032	Tensile (MPa)	554,000	Tensile (ksi)	80,351
Heat Code:	BND32C26	Sulfur (S)	0.013	Silicon (Si)	0.450	Copper (Cu)	0.027	Yield (MPa)	387,000	Yield (ksi)	55,130
ASTM Code:	A216-08-WCB	Nickel (Ni)	0.027	Chromium (Cr)	0.038	Molybdenum (Mo)	0.004	Elongation (%)	28.400	Reduction Of Area (%)	53.000
Description:	BODY	Vanadium (V)	0.007					Heat Treatment	NORMALIZED		
		C.E.	0.354								

MECHANICALS

Supplier:	BN	Carbon (C)	0.195	Manganese (Mn)	0.443	Phosphorus (P)	0.024	Tensile (MPa)	554,000	Tensile (ksi)	80,351
Heat Code:	BND32C26	Sulfur (S)	0.011	Silicon (Si)	0.438	Copper (Cu)	0.042	Yield (MPa)	359,000	Yield (ksi)	52,069
ASTM Code:	A216-08-WCB	Nickel (Ni)	0.041	Chromium (Cr)	0.060	Molybdenum (Mo)	0.004	Elongation (%)	33.000	Reduction Of Area (%)	54.900
Description:	BODY	Vanadium (V)	0.008					Heat Treatment	NORMALIZED		
		C.E.	0.355								

Supplier:	BN	Carbon (C)	0.187	Manganese (Mn)	0.971	Phosphorus (P)	0.024	Tensile (MPa)	559,000	Tensile (ksi)	81,076
Heat Code:	BND32C20	Sulfur (S)	0.006	Silicon (Si)	0.421	Copper (Cu)	0.027	Yield (MPa)	371,000	Yield (ksi)	53,809
ASTM Code:	A216-08-WCB	Nickel (Ni)	0.026	Chromium (Cr)	0.045	Molybdenum (Mo)	0.006	Elongation (%)	33.000	Reduction Of Area (%)	54.900
Description:	BONNET	Vanadium (V)	0.007					Heat Treatment	NORMALIZED		
		C.E.	0.364								

Supplier:	BN	Carbon (C)	0.197	Manganese (Mn)	0.885	Phosphorus (P)	0.033	Tensile (MPa)	611,000	Tensile (ksi)	88,618
Heat Code:	BND32D01	Sulfur (S)	0.010	Silicon (Si)	0.440	Copper (Cu)	0.031	Yield (MPa)	429,000	Yield (ksi)	60,916
ASTM Code:	A216-08-WCB	Nickel (Ni)	0.038	Chromium (Cr)	0.037	Molybdenum (Mo)	0.004	Elongation (%)	26.800	Reduction Of Area (%)	45.000
Description:	BONNET	Vanadium (V)	0.008					Heat Treatment	NORMALIZED		
		C.E.	0.339								

Supplier:	BN	Carbon (C)	0.201	Manganese (Mn)	0.984	Phosphorus (P)	0.032	Tensile (MPa)	554,000	Tensile (ksi)	80,351
Heat Code:	BND32D04	Sulfur (S)	0.012	Silicon (Si)	0.458	Copper (Cu)	0.028	Yield (MPa)	355,000	Yield (ksi)	51,468
ASTM Code:	A216-08-WCB	Nickel (Ni)	0.021	Chromium (Cr)	0.035	Molybdenum (Mo)	0.006	Elongation (%)	28.400	Reduction Of Area (%)	55.000
Description:	BODY	Vanadium (V)	0.007					Heat Treatment	NORMALIZED		
		C.E.	0.378								

CHEMICALS

MECHANICALS

Supplier: BN	Carbon (C)	0.189	Manganese (Mn)	0.573	Phosphorus (P)	0.029	Tensile (MPa)	555,000	Tensile (ksi)	80.4%
Heat Code: BND33D02	Sulfur (S)	0.010	Silicon (Si)	0.404	Copper (Cu)	0.031	Yield (MPa)	350,000	Yield (ksi)	50.763
ASTM Code: A216-08-WCB	Nickel (Ni)	0.023	Chromium (Cr)	0.018	Molybdenum (Mo)	0.005	Elongation (%)	35.400	Reduction Of Area (%)	59.100
Description: BONNET	Vanadium (V)	0.008					Heat Treatment	NORMALIZED		
	C.E.	0.348								

Supplier: BN	Carbon (C)	0.199	Manganese (Mn)	0.931	Phosphorus (P)	0.032	Tensile (MPa)	388,000	Tensile (ksi)	55.202
Heat Code: BND33D06	Sulfur (S)	0.011	Silicon (Si)	0.426	Copper (Cu)	0.040	Yield (MPa)	379,000	Yield (ksi)	54.969
ASTM Code: A216-08-WCB	Nickel (Ni)	0.041	Chromium (Cr)	0.051	Molybdenum (Mo)	0.004	Elongation (%)	35.000	Reduction Of Area (%)	57.000
Description: BONNET	Vanadium (V)	0.009					Heat Treatment	NORMALIZED		
	C.E.	0.372								

Supplier: BN	Carbon (C)	0.200	Manganese (Mn)	0.890	Phosphorus (P)	0.032	Tensile (MPa)	559,000	Tensile (ksi)	81.076
Heat Code: BND33D08	Sulfur (S)	0.011	Silicon (Si)	0.403	Copper (Cu)	0.040	Yield (MPa)	363,000	Yield (ksi)	52.449
ASTM Code: A216-08-WCB	Nickel (Ni)	0.044	Chromium (Cr)	0.039	Molybdenum (Mo)	0.005	Elongation (%)	34.000	Reduction Of Area (%)	62.100
Description: BONNET	Vanadium (V)	0.009					Heat Treatment	NORMALIZED		
	C.E.	0.369								

Supplier: BN	Carbon (C)	0.200	Manganese (Mn)	0.868	Phosphorus (P)	0.033	Tensile (MPa)	597,000	Tensile (ksi)	86.584
Heat Code: BND33D10	Sulfur (S)	0.010	Silicon (Si)	0.439	Copper (Cu)	0.030	Yield (MPa)	375,000	Yield (ksi)	54.189
ASTM Code: A216-08-WCB	Nickel (Ni)	0.023	Chromium (Cr)	0.037	Molybdenum (Mo)	0.004	Elongation (%)	36.000	Reduction Of Area (%)	61.000
Description: BODY	Vanadium (V)	0.007					Heat Treatment	NORMALIZED		
	C.E.	0.356								

Supplier: BN	Carbon (C)	0.195	Manganese (Mn)	0.851	Phosphorus (P)	0.031	Tensile (MPa)	567,000	Tensile (ksi)	82.236
Heat Code: BND34D02	Sulfur (S)	0.010	Silicon (Si)	0.438	Copper (Cu)	0.035	Yield (MPa)	367,000	Yield (ksi)	53.229
ASTM Code: A216-08-WCB	Nickel (Ni)	0.039	Chromium (Cr)	0.043	Molybdenum (Mo)	0.006	Elongation (%)	34.000	Reduction Of Area (%)	62.100
Description: BONNET	Vanadium (V)	0.009					Heat Treatment	NORMALIZED		
	C.E.	0.353								

CHEMICALS

MECHANICALS

Certificate #: 74756

Supplier: BN		Carbon (C)	0.201	Manganese (Mn)	0.382	Phosphorous (P)	0.023	Tensile (ksi)	80,206
Heat Code: BND34D04		Sulfur (S)	0.011	Silicon (Si)	0.428	Copper (Cu)	0.032	Yield (ksi)	54,969
ASTM Code: A216-08-WCB		Nickel (Ni)	0.031	Chromium (Cr)	0.049	Molybdenum (Mo)	0.006	Elongation (%)	35,000
Description: BODY		Vanadium (V)	0.008					Reduction Of Area (%)	60,100
		C.E.	0.364					Heat Treatment: NORMALIZED	
Supplier: UN		Carbon (C)	0.187	Manganese (Mn)	0.357	Phosphorous (P)	0.034	Tensile (ksi)	81,801
Heat Code: BND34D10		Sulfur (S)	0.016	Silicon (Si)	0.452	Copper (Cu)	0.039	Yield (ksi)	52,069
ASTM Code: A216-08-WCB		Nickel (Ni)	0.035	Chromium (Cr)	0.061	Molybdenum (Mo)	0.005	Elongation (%)	34,000
Description: BODY		Vanadium (V)	0.007					Reduction Of Area (%)	58,000
		C.E.	0.366					Heat Treatment: NORMALIZED	
Supplier: DN		Carbon (C)	0.201	Manganese (Mn)	0.332	Phosphorous (P)	0.028	Tensile (ksi)	83,977
Heat Code: BND36C16		Sulfur (S)	0.012	Silicon (Si)	0.413	Copper (Cu)	0.034	Yield (ksi)	58,130
ASTM Code: A216-08-WCB		Nickel (Ni)	0.030	Chromium (Cr)	0.055	Molybdenum (Mo)	0.004	Elongation (%)	33,100
Description: BODY		Vanadium (V)	0.008					Reduction Of Area (%)	54,800
		C.E.	0.374					Impact Energy 1 (FT-LB)	35,403
								Impact Energy 2 (FT-LB)	35,403
								Impact Energy 3 (FT-LB)	35,403
								Impact Energy 4 (J)	48,000
								Impact Energy 5 (J)	48,000
								Temperature (°C)	-20,200
								Heat Treatment: QUEN & TEMP	

Velan certifies that all valve(s) described above are in compliance with purchase order and specification requirements.

Sasha Foster

Sasha Foster

01-AUG-2013



Manager of Q.C. Documentation

Date

Customer Representative

Date

NLIA-DPH-2001
CPD#51 GF-03A00

YANCHENG H & M PRESSURE VALVE CO.,LTD										MATERIAL CERTIFICATE										Certificate No: KF-1401-01			
No.6 Juheng Road Economic development Zone Yancheng City, China										(BS EN 10204.3.1)										Certificate Date: 2014/01/13			
Tel: +86-515-8281015 Fax: +86-515-8281003 E-mail: ygj@public.yc.js.cn										Customer: KF Description: GATE VALVE#300LB										P/O No: P31240 CAT No:GA0301XU-8-GO		QTY: 2 Material: ASTM A216 WCB	
Name of Parts		Heat No.		CHEMICAL ANALYSIS (%) MAX										MECHANICAL PROPERTIES									
		C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	Others	Tensile	Yield	Elongation	Reduction	Hardness						
		0.3 Max.	1.0 Max.	0.035 Max.	0.035 Max.	0.6 Max.	0.3 Max.	0.5 Max.	0.5 Max.	0.2 Max.	0.03 Max.		485-655 Mpa	250Min. MPa	22% Min.	35% Min.	HB						
BODY	A60624	0.204	0.860	0.028	0.019	0.451	0.049	0.057	0.175	0.025	0.005		519	272	29	36	169						
BONNET	A60713	0.191	0.760	0.031	0.023	0.463	0.040	0.049	0.120	0.020	0.006		520	258	25	38	166						
BONNET	A60624	0.204	0.860	0.028	0.019	0.451	0.049	0.057	0.175	0.025	0.005		519	272	29	36	169						
WEDGE	A60612	0.213	0.700	0.028	0.020	0.451	0.046	0.055	0.151	0.024	0.004		510	266	32	37	164						
WEDGE	A60627	0.211	0.750	0.026	0.022	0.470	0.047	0.053	0.202	0.022	0.006		523	270	29	40	168						
HEAT TREATMENT		REMARKS										Signature / Date		Inspector									
Normalizing		We hereby certify that the materials described above have been tested and comply to the material specifications of the purchase order.																					

YANCHENG H & M PRESSURE VALVE CO.,LTD

**No.6 Juheng Road Economic development Zone Yancheng City,
China**

MATERIAL CERTIFICATE

(BS EN 10204 2.2)

Certificate No: KF-1401-01

5Certificate Date: 2014/01/13

Tel: +86-515-8281015 Fax: +86-515-8281015

Customer: KF

P/O No: P31240

QTY: 2

E-mail: yaf@public.cc.is.cn

Description: GATE VALVE8"300LB

CAT No:GA03011XU-8"-GO

CHEMICAL ANALYSIS (%) MAX

MECHANICAL PROPERTIES

[illegible]

REMARKS

Signature / Date

Inspector

We hereby certify that the materials described above have been tested and comply to the material specifications of the purchase order.

CPD # 51

NO.6 Juheng Road, Economic Development Zone, Yancheng City, China

Tel: +86-515-8281015 Fax: +86-515-8281015 E-mail: ygf@public.yc.js.cn

Certificate No: KF-1401-09

DATE: 2014.01.16

SHEET 1 OF 1

PRESSURE TEST CERTIFICATE

Pressure Test (As per API 598)					Name of Valves: GATE VALVE						
Item	Test Pressure (MPa)	Test Durations (Sec.)	Allowable Leakage Rate (max)	Result	Size & Class: 8" 300 LB	Quantity: 5	Valve Material: ASTM A216 WCB	PO No.: P31240	CAT No.: GA03011XU-8"-GO	Valve requirement	
										Shell Test	Backseat Test
	7.8	120	0	OK						API600 (✓)	BS1873 ())
	5.8	60	0	OK						BS1868 ()	NACE MR 0175 ()
	5.8	120	0	OK							
	0.6	120	0	OK							

Serial No.		Heat No.						Lot No.	
Body	Bonnet	Wedge	Seat Ring	Stem	Back Seat	Bolt	Nut		
KF813100362 ✓	A60624	A60620	A60627	A13067	S13082	T41012	...	...	...
KF813100363 ✓	A60713	A60711	A60617	A13067	S13082	T41012	...	...	...
KF813100364 ✓	A60713	A60713	A60612	A13067	S13082	T41012	...	...	...
KF813100365	A60711	A60624	A60624	A13067	S13082	T41012	...	...	...
KF813100366 ✓	A60620	A60620	A60612	A13067	S13082	T41012	...	...	...

YANCHENG H & M PRESSURE VALVE CO.,LTD										MATERIAL CERTIFICATE										Certificate No: KF-1401-09			
No.6 Juheng Road Economic development Zone Yancheng City, China										(BS EN 10204.3.1)										Certificate Date: 2014/01/16			
Tel: +86-515-8281015 Fax: +86-515-8281003										Customer: KF										P/O No: P31240		QTY: 5	
E-mail: yqf@public.yc.js.cn										Description: GATE VALVE#300LB										CAT No:GA03011XU-8"-GO		Sheet 1 of 2	
CHEMICAL ANALYSIS (%) MAX										MECHANICAL PROPERTIES													
Name of Parts	Heat No.	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	Others	Tensile 485-655 Mpa	Yield 250Min. MPa	Elongation 22% Min.	Reduction 35% Min.	Hardness HB						
		0.3 Max.	1.0 Max.	0.035 Max.	0.035 Max.	0.6 Max.	0.3 Max.	0.5 Max.	0.5 Max.	0.2 Max.	0.03 Max.												
BODY	✓ A60624	0.204	0.860	0.028	0.019	0.451	0.049	0.057	0.175	0.025	0.005		519	272	29	36	169						
BODY	✓ A60713	0.191	0.760	0.031	0.023	0.463	0.040	0.049	0.120	0.020	0.006		520	258	25	38	166						
BODY	✓ A60711	0.206	0.800	0.035	0.025	0.488	0.045	0.050	0.138	0.025	0.002		508	258	27	39	168						
BODY	✓ A60620	0.190	0.750	0.027	0.018	0.414	0.049	0.055	0.158	0.024	0.006		509	260	24	37	159						
BONNET	✓ A60624	0.204	0.860	0.028	0.019	0.451	0.049	0.057	0.175	0.025	0.005		519	272	29	36	169						
BONNET	✓ A60713	0.191	0.760	0.031	0.023	0.463	0.040	0.049	0.120	0.020	0.006		520	258	25	38	166						
BONNET	✓ A60711	0.206	0.800	0.035	0.025	0.488	0.045	0.050	0.138	0.025	0.002		508	258	27	39	168						
BONNET	✓ A60620	0.190	0.750	0.027	0.018	0.414	0.049	0.055	0.158	0.024	0.006		509	260	24	37	159						
WEDGE	A60612	0.213	0.700	0.028	0.020	0.451	0.046	0.055	0.151	0.024	0.004		510	266	32	37	164						
WEDGE	A60627	0.211	0.750	0.026	0.022	0.470	0.047	0.053	0.202	0.022	0.006		523	270	29	40	168						
WEDGE	A60624	0.204	0.860	0.028	0.019	0.451	0.049	0.057	0.175	0.025	0.005		519	272	29	36	169						
WEDGE	A60617	0.185	0.780	0.032	0.023	0.459	0.054	0.063	0.176	0.028	0.007		511	256	25	36	170						
HEAT TREATMENT																							
Normalizing																							
REMARKS																							
We hereby certify that the materials described above have been tested and comply to the material specifications of the purchase order.																							
Signature / Date															Inspector								



Certificate of Conformance

OA line 1 CPO# 20
Page 1 of 1

Certificate #: 143460

Plant 4 Velan Inc.
1010 Cowie Street
Granby, Quebec
Canada, J2L 1E7
Phone : 450-378-2305
Fax : 450-378-6865

Customer Name : MRC GLOBAL COMPANY
Customer Po # : N/A
Velan Order # : 014-999999-
Valve Design : B16.34
Hydro Test Spec : API-598
Test Result : ACCEPTABLE

Certificate Date : 08-DEC-2014
Item Number : 1
Quantity : 2
Figure Number : F-1064C-02TY
Description : 6" 300# CS BB GATE VLV
Draw No. & Rev : REV

NOTES :

MATERIAL TEST RESULTS SHOWN BELOW:

CHEMICALS

ASTM Code: A216-08-WCB-

Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC04L10	BODY	0.209	0.954	0.028	0.008	0.481	0.041	0.026	0.042	0.004	0.006	542.0 / 78.6	342.0 / 49.6	30.6	60.0	/
Heat Treatment		C.E.										Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED		.3829										/	/	/	/	/
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC09B02	BONNET	0.199	0.936	0.023	0.008	0.494	0.035	0.048	0.038	0.004	0.007	546.0 / 79.2	346.0 / 50.2	29.2	54.0	/
Heat Treatment		C.E.										Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED		.3703										/	/	/	/	/
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND16C12	BODY	0.194	0.899	0.033	0.009	0.427	0.029	0.027	0.042	0.004	0.007	584.0 / 84.7	398.0 / 57.7	34.4	58.0	/
Heat Treatment		C.E.										Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED		.3582										/	/	/	/	/

Velan hereby certifies that the valve(s) described above is (are) in conformance with the purchase order and specification requirements. The test report represents the actual attributes of items furnished and all test results are in full conformance with applicable specification and purchase order requirements.


Sallie Beresford for
Velan

08-DEC_2014
Date

Customer Representative
Date

VL1A-DP14-2001
CPO# 20 GF-03A00



Certificate of Conformance

CA line 2 CPO# 36

Certificate #: P4-132758

Plant 4 Velan Inc.
1010 Cowie Street
Granby, Quebec
Canada, J2J 1E7
Phone : 450-378-2305
Fax : 450-378-6865

Customer Name : MRC CANADA ULC.
Customer Po # : S7SH218462
Velan Order # : M014-869527-W
Valve Design : API-600
Hydro Test Spec : API-600
Test Result : ACCEPTABLE

NOTES : ALL TESTS AND EXAMINATIONS MEET EN 10204-3.1/ ISO 10474-3.1
MATERIAL TEST RESULTS SHOWN BELOW:

CHEMICALS

ASTM Code: A216-08-WCB-

MECHANICALS [F/B: Flattening/ bending; GS: Grain size]

Certificate Date : 03-JUL-2013
Item Number : 09
Quantity : 31
Figure Number : F14-1064C-02TY-W320
Description : VALVE 6" 300 GATE RF
Draw No. & Rev : REV

Tag Number(s) : NONE

Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC04G01	BONNET	0.202	0.917	0.031	0.014	0.409	0.036	0.047	0.045	0.004	0.007	546.0 / 79.2	342.0 / 49.6	31.2	52.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC04G02	BONNET	0.198	0.903	0.030	0.010	0.473	0.039	0.048	0.047	0.007	0.007	567.0 / 82.2	359.0 / 52.1	29.4	47.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC06K04	BODY	0.202	0.902	0.029	0.010	0.483	0.041	0.047	0.065	0.006	0.011	546.0 / 79.2	350.0 / 50.8	28.8	60.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC07K02	BODY	0.190	0.968	0.019	0.016	0.500	0.046	0.069	0.142	0.010	0.006	591.0 / 85.7	387.0 / 56.1	28.8	49.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC09C22	BONNET	0.201	0.918	0.022	0.007	0.436	0.031	0.035	0.052	0.003	0.006	562.0 / 81.5	367.0 / 53.2	29.6	56.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC12D14	BONNET	0.202	0.949	0.035	0.011	0.413	0.038	0.048	0.047	0.005	0.008	546.0 / 79.2	346.0 / 50.2	30.6	60.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC15C16	BONNET	0.195	0.976	0.031	0.012	0.486	0.038	0.040	0.044	0.006	0.007	566.0 / 82.1	355.0 / 51.5	27.8	49.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		

NL1A-BPH-2001
CPO#36 GF-03A00

Heat Code	Dese	(C)	(Mo)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC15H03	BONNET	0.207	0.929	0.032	0.010	0.473	0.042	0.053	0.050	0.007	0.008	550.0 / 79.8	346.0 / 50.2	29.0	56.0	/
Heat Treatment	NORMALIZED											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
Heat Code	Dese	(C)	(Mo)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC17H29	BONNET	0.204	0.955	0.029	0.008	0.422	0.039	0.050	0.050	0.005	0.006	583.0 / 84.6	379.0 / 55.0	27.2	49.0	/
Heat Treatment	NORMALIZED											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
Heat Code	Dese	(C)	(Mo)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC23C30	BONNET	0.194	0.969	0.025	0.008	0.453	0.036	0.069	0.048	0.007	0.007	575.0 / 83.4	367.0 / 53.2	29.6	55.0	/
Heat Treatment	NORMALIZED											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
Heat Code	Dese	(C)	(Mo)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND01A02	BODY	0.192	0.981	0.025	0.008	0.416	0.030	0.027	0.048	0.004	0.006	595.0 / 86.3	403.0 / 58.5	26.8	49.0	/
Heat Treatment	NORMALIZED											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
Heat Code	Dese	(C)	(Mo)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND01C06	BODY	0.185	0.902	0.031	0.010	0.408	0.033	0.033	0.047	0.005	0.007	579.0 / 84.0	377.0 / 54.7	32.6	58.0	/
Heat Treatment	NORMALIZED											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
Heat Code	Dese	(C)	(Mo)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND01C08	BODY	0.201	0.927	0.033	0.016	0.442	0.032	0.034	0.041	0.004	0.007	569.0 / 82.5	368.0 / 53.4	33.4	60.1	/
Heat Treatment	NORMALIZED											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
Heat Code	Dese	(C)	(Mo)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND01C09	BODY	0.203	0.894	0.028	0.012	0.409	0.035	0.039	0.047	0.007	0.007	573.0 / 83.1	367.0 / 53.2	33.0	60.1	/
Heat Treatment	NORMALIZED											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
Heat Code	Dese	(C)	(Mo)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND02A17	BODY	0.196	0.900	0.025	0.011	0.485	0.040	0.067	0.046	0.006	0.010	567.0 / 82.2	367.0 / 53.2	28.4	52.0	/
Heat Treatment	NORMALIZED											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
Heat Code	Dese	(C)	(Mo)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND02C06	BODY	0.189	0.870	0.027	0.009	0.443	0.038	0.034	0.051	0.007	0.007	580.0 / 84.1	367.0 / 53.2	30.2	61.1	/
Heat Treatment	NORMALIZED											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS

Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND02C07	BODY	0.193	0.937	0.031	0.010	0.460	0.037	0.035	0.042	0.005	0.008	582.0 / 84.4	387.0 / 56.1	31.4	58.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND02C09	BODY	0.186	0.891	0.029	0.013	0.396	0.025	0.023	0.037	0.004	0.007	549.0 / 79.6	342.0 / 49.6	32.6	57.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND02D27	BODY	0.187	0.868	0.030	0.009	0.444	0.037	0.120	0.047	0.005	0.009	574.0 / 83.3	371.0 / 53.8	35.4	57.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND03C08	BODY	0.201	0.847	0.031	0.011	0.393	0.040	0.031	0.047	0.005	0.007	575.0 / 83.4	363.0 / 52.6	34.2	58.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND03C09	BODY	0.202	0.906	0.028	0.010	0.442	0.034	0.039	0.060	0.011	0.008	611.0 / 88.6	395.0 / 57.3	35.0	54.9	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND03C27	BODY	0.200	0.904	0.033	0.011	0.443	0.042	0.041	0.047	0.005	0.009	580.0 / 84.1	355.0 / 51.5	36.0	61.1	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND04C03	BONNET	0.190	0.830	0.027	0.009	0.417	0.038	0.038	0.040	0.005	0.009	547.0 / 79.3	330.0 / 47.9	31.6	62.1	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND04C08	BODY	0.189	0.912	0.023	0.009	0.405	0.037	0.031	0.045	0.005	0.008	583.0 / 84.6	391.0 / 56.7	32.0	63.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND04C09	BONNET	0.209	0.835	0.034	0.011	0.455	0.035	0.035	0.049	0.006	0.008	585.0 / 84.8	359.0 / 52.1	32.6	61.1	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/		

Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND05C23	BONNET	0.196	0.937	0.033	0.011	0.450	0.030	0.028	0.042	0.004	0.008	570.0 / 82.7	364.0 / 52.8	31.4	58.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/		/		
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND09C22	BONNET	0.192	0.858	0.025	0.010	0.394	0.028	0.027	0.041	0.004	0.007	579.0 / 84.0	387.0 / 56.1	28.6	53.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/		/		
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND10C17	BODY	0.188	0.928	0.028	0.009	0.427	0.026	0.022	0.032	0.004	0.007	577.0 / 83.7	375.0 / 54.4	30.6	58.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/		/		
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND11C18	BONNET	0.187	0.878	0.027	0.008	0.434	0.033	0.026	0.037	0.005	0.008	578.0 / 83.8	376.0 / 54.5	31.8	57.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/		/		
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND12C15	BODY	0.196	0.852	0.032	0.010	0.415	0.031	0.027	0.048	0.004	0.008	567.0 / 82.2	367.0 / 53.2	33.4	58.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/		/		
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND13C15	BODY	0.202	0.936	0.029	0.009	0.476	0.033	0.041	0.039	0.006	0.016	542.0 / 78.6	338.0 / 49.0	28.6	52.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/		/		
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND13C17	BODY	0.193	0.906	0.031	0.009	0.472	0.027	0.027	0.039	0.004	0.009	584.0 / 84.7	379.0 / 55.0	32.6	61.1	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/		/		
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND14C14	BONNET	0.201	0.885	0.030	0.012	0.422	0.024	0.021	0.064	0.004	0.007	587.0 / 85.1	387.0 / 56.1	28.6	49.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/		/		
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND14C15	BODY	0.194	0.870	0.029	0.010	0.458	0.025	0.021	0.033	0.004	0.006	558.0 / 80.9	359.0 / 52.1	28.6	54.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/		/		

Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND14C19	BODY	0.187	0.863	0.033	0.010	0.497	0.031	0.025	0.038	0.004	0.008	552.0 / 80.1	365.0 / 52.6	31.4	62.1	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND15C14	BONNET	0.185	0.852	0.034	0.010	0.440	0.030	0.027	0.046	0.005	0.007	560.0 / 81.2	363.0 / 52.6	32.4	58.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND15C15	BONNET	0.188	0.982	0.024	0.008	0.413	0.029	0.034	0.033	0.004	0.014	568.0 / 82.4	367.0 / 53.2	30.6	58.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND15C16	BONNET	0.192	0.935	0.034	0.010	0.433	0.029	0.029	0.056	0.004	0.007	573.0 / 83.1	379.0 / 55.0	32.2	58.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND15C17	BONNET	0.193	0.875	0.029	0.009	0.462	0.027	0.027	0.038	0.007	0.008	564.0 / 81.8	358.0 / 51.9	34.2	57.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND16C13	BODY	0.189	0.892	0.032	0.007	0.429	0.029	0.026	0.036	0.004	0.008	580.0 / 84.1	383.0 / 55.5	34.0	62.1	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND16D12	BODY	0.200	0.945	0.028	0.009	0.416	0.032	0.024	0.045	0.005	0.007	556.0 / 80.6	322.0 / 46.7	31.6	62.1	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND17A06	BODY	0.192	0.881	0.030	0.011	0.454	0.036	0.027	0.048	0.005	0.005	591.0 / 85.7	338.0 / 49.0	27.2	58.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1	29.0	56.0	/
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND19C13	BODY	0.186	0.968	0.029	0.010	0.390	0.027	0.026	0.053	0.005	0.007	567.0 / 82.2	359.0 / 52.1			

Velan hereby certifies that the valve(s) described above is (are) in conformance with the purchase order and specification requirements. The test report represents the actual attributes of items furnished and all test results are in full conformance with applicable specification and purchase order requirements.

Gilles Delafontaine for

Velan

Date _____

03-JUL-2013

Customer Representative

Date _____

Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)
BND19C15	BODY	0.194	0.907	0.029	0.012	0.391	0.029	0.031	0.046	0.005	0.011
Heat Treatment	NORMALIZED										
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)
BND25C20	BONNET	0.202	0.913	0.035	0.015	0.429	0.029	0.022	0.037	0.004	0.008
Heat Treatment	NORMALIZED										
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)
BND33D03	BODY	0.189	0.908	0.030	0.009	0.473	0.030	0.033	0.043	0.005	0.009
Heat Treatment	NORMALIZED										
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)
BND33B03	BONNET	0.189	0.931	0.031	0.008	0.414	0.034	0.034	0.044	0.009	0.008
Heat Treatment	NORMALIZED										
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)							
567.0 / 82.2	351.0 / 50.9	29.6	56.0	/							
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B	GS						
/	/	/	/								
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)							
587.0 / 85.1	395.0 / 57.3	30.4	58.0	/							
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B	GS						
/	/	/	/								
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)							
570.0 / 82.7	350.0 / 50.8	33.2	54.9	/							
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B	GS						
/	/	/	/								
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)							
570.0 / 82.7	326.0 / 47.3	30.8	61.0	/							
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B	GS						
/	/	/	/								



Certificate of Conformance

OA line 2 CPO# 36

Certificate #: 143460

Plant 4 Velan Inc.
1010 Cowie Street
Granby, Quebec
Canada, J2J 1E7
Phone : 450-378-2305
Fax : 450-378-6865

Customer Name : MRC GLOBAL COMPANY
Customer Po # : N/A
Velan Order # : 014-999999-
Valve Design : B16.34
Hydro Test Spec : API-598
Test Result : ACCEPTABLE

Certificate Date : 08-DEC-2014
Item Number : 1
Quantity : 2
Figure Number : F-1064C-02TY
Description : 6" 300# CS BB GATE VLV
Draw No. & Rev : REV

NOTES :

MATERIAL TEST RESULTS SHOWN BELOW:

CHEMICALS

ASTM Code: A216-08-WCB-

Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND04L10	BODY	0.209	0.954	0.028	0.008	0.481	0.041	0.026	0.042	0.004	0.006	542.0 / 78.6	342.0 / 49.6	30.6	60.0	/
Heat Treatment		C.E.										Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/	/	
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNC09B02	BONNET	0.199	0.936	0.023	0.008	0.494	0.035	0.048	0.038	0.004	0.007	546.0 / 79.2	346.0 / 50.2	29.2	54.0	/
Heat Treatment		C.E.										Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/	/	
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND16C12	BODY	0.194	0.899	0.033	0.009	0.427	0.029	0.027	0.042	0.004	0.007	584.0 / 84.7	398.0 / 57.7	34.4	58.0	/
Heat Treatment		C.E.										Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
NORMALIZED												/	/	/	/	

Velan hereby certifies that the valve(s) described above is (are) in conformance with the purchase order and specification requirements. The test report represents the actual attributes of items furnished and all test results are in full conformance with applicable specification and purchase order requirements.

Satire Beresford for
Velan
08-DEC_2014
Date

Customer Representative
Date

VELAN

Certificate of Conformance

QA Line 1 CP0# 44 13

Page 1 of 1

Plant 4 Velan Inc
1018 Cowie Street
Granby, Quebec
Canada, J2J 1E7
Phone : 450-378-2305
Fax : 450-378-6865

Customer Name: MRC CANADA ULC
Customer Po #: 5759234007
Velan Order #: M014-870277-W
Valve Design: API-600
Hydro Test Spec: API-600
Test Result: ACCEPTABLE

NOTES : ALL TESTS AND EXAMINATIONS MEET EN 10204-3.1 ISO 10474-3.1
MATERIAL TEST RESULTS SHOWN BELOW:

CHEMICALS

ASTM Code: A316-05-WCB

Heat Code Desc (C) (Mn) (P) (S) (Si) (Cu) (Ni) (Cr) (Mo) (V)
BND02E29 BONNET 0.196 0.045 0.027 0.007 0.394 0.027 0.102 0.045 0.005 0.009
Heat Treatment
NORMA(L)ZED

Heat Code Desc (C) (Mn) (P) (S) (Si) (Cu) (Ni) (Cr) (Mo) (V)
BND02E30 BODY 0.193 0.875 0.032 0.010 0.441 0.039 0.046 0.043 0.007 0.008
Heat Treatment
NORMA(L)ZED

Heat Code Desc (C) (Mn) (P) (S) (Si) (Cu) (Ni) (Cr) (Mo) (V)
BND02E28 BONNET 0.189 0.940 0.024 0.007 0.474 0.042 0.012 0.045 0.025 0.010
Heat Treatment
NORMA(L)ZED

Heat Code Desc (C) (Mn) (P) (S) (Si) (Cu) (Ni) (Cr) (Mo) (V)
BND02E07 BONNET 0.192 0.841 0.029 0.009 0.450 0.032 0.032 0.042 0.004 0.006
Heat Treatment
NORMA(L)ZED

Heat Code Desc (C) (Mn) (P) (S) (Si) (Cu) (Ni) (Cr) (Mo) (V)
BND02E06 BODY 0.201 0.957 0.034 0.009 0.462 0.033 0.042 0.038 0.006 0.009
Heat Treatment
NORMA(L)ZED

Heat Code Desc (C) (Mn) (P) (S) (Si) (Cu) (Ni) (Cr) (Mo) (V)
BND11E27 BODY 0.195 0.880 0.030 0.009 0.494 0.032 0.048 0.052 0.007 0.009
Heat Treatment
NORMA(L)ZED

Heat Code Desc (C) (Mn) (P) (S) (Si) (Cu) (Ni) (Cr) (Mo) (V)
BND12D13 BONNET 0.200 0.012 0.026 0.009 0.427 0.040 0.040 0.076 0.009 0.009
Heat Treatment
NORMA(L)ZED

Certificate Date: 26-SEP-2013
Item Number: 01
Quantity: 26
Figure Number: F10-006-0C-02TY-W320
Description: VALVE 3" 150 GA TE RF
Draw No. & Rev: REV
Tag Number(s): NONE

Certificate #: PA134551

Position No: 5

MECHANICALS [F/B: Flattening/ bending; GS: Grain size]

Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
562.0 / 81.5	379.0 / 54.0	35.0	58.0	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
/	/	/	/	/
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
565.0 / 81.9	367.4 / 53.2	35.0	58.0	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
/	/	/	/	/
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
551.0 / 79.0	371.0 / 53.8	36.0	62.1	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
/	/	/	/	/
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
551.0 / 79.9	359.0 / 52.1	33.0	58.0	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
/	/	/	/	/
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
575.0 / 83.4	370.0 / 53.0	36.0	57.0	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
/	/	/	/	/
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
579.0 / 84.0	379.0 / 54.0	33.0	62.1	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
/	/	/	/	/
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
519.0 / 75.3	322.0 / 46.7	36.4	62.1	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
/	/	/	/	/

NL1A - DPH-2001
C00#44 GF-01ABD

Heat Code	Desc	(C)	(Mn)	(P)	(S)	(SI)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa/ksi)	Yield (MPa/ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
BND310E24	BONNET	0.200	0.968	0.034	0.010	0.413	0.036	0.037	0.039	0.006	0.009	580.0 / 84.1	375.0 / 54.4	35.0	58.0	F/B CS
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(SI)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa/ksi)	Yield (MPa/ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
BND31E17	BODY	0.190	0.871	0.028	0.010	0.425	0.038	0.061	0.070	0.019	0.009	562.0 / 81.5	367.0 / 53.2	31.0	57.0	F/B CS
Heat Treatment																
NORMALIZED																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(SI)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa/ksi)	Yield (MPa/ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
BND31E20	BODY	0.186	0.835	0.032	0.010	0.464	0.035	0.044	0.048	0.006	0.008	565.0 / 81.9	342.0 / 49.6	36.0	62.1	F/B CS
Heat Treatment																
NORMALIZED																

Velan hereby certifies that the valve(s) described above is (are) in conformance with the purchase order and specification requirements. The test report represents the actual attributes of items furnished and all test results are in full conformance with applicable specification and purchase order requirements.

Bill Bruck
Gilles Quentin for

Date 26-SEP-2013

Customer Representative

Date



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 50421-1030(80278099)

DATE: 2014.12.6

PAGE: 7 OF 8

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.									
WCB	NORMALIZE	920-940 (1688-1724°F)	1H/25MM	AIR	GAS										

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS													MECHANICAL PROPERTIES									
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (JOULE)			
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%			HB	TEMP °C	Avg	Min
		MAX.	0.23	1.28	0.6	0.03	0.035	0.5	0.5	0.2	0.3	0.03					655					237			
		MIN.															485	250	22	35	135				

WEDGE	WCB	61A30	0.18	0.77	0.45	0.01	0.016	0.088	0.038	0.02	0.024	0.001				0.334	495	315	37	64	171			
WEDGE	WCB	51A57	0.19	0.84	0.49	0.01	0.017	0.086	0.053	0.011	0.023	0.001				0.355	495	340	36	62	170			
BODY	WCB	F3855	0.194	0.987	0.45	0.01	0.021	0.099	0.028	0.008	0.01	0.002				0.383	530	350	30	45	163			
BONNET	WCB	F3827	0.194	0.993	0.443	0.007	0.027	0.193	0.051	0.021	0.017	0.005				0.408	540	350	28	49	170			
BONNET	WCB	F3644	0.207	1.068	0.413	0.008	0.027	0.112	0.039	0.013	0.018	0.004				0.415	560	365	28	40	170			
BODY	WCB	F3872	0.194	1.011	0.482	0.008	0.028	0.139	0.044	0.015	0.02	0.005				0.399	525	275	28	47	163			
BODY	WCB	F3854	0.186	1.013	0.414	0.009	0.023	0.13	0.045	0.015	0.018	0.004				0.389	530	355	30	41	163			
BONNET	WCB	F3825	0.194	0.979	0.398	0.008	0.031	0.116	0.049	0.014	0.019	0.004				0.389	525	345	28	46	163			
BODY	WCB	F3857	0.184	1.095	0.457	0.006	0.026	0.099	0.032	0.012	0.017	0.003				0.393	540	355	30	49	170			
BODY	WCB	F3828	0.195	1.057	0.413	0.008	0.026	0.075	0.026	0.007	0.014	0.004				0.391	535	350	29	42	159			
BODY	WCB	F3870	0.194	1.04	0.427	0.006	0.023	0.18	0.07	0.026	0.019	0.005				0.415	550	335	28	52	179			
BODY	WCB	F3711	0.188	1.021	0.418	0.008	0.026	0.134	0.053	0.017	0.017	0.004				0.394	530	345	28	41	170			
BONNET	WCB	F3761	0.197	1.015	0.426	0.007	0.029	0.082	0.032	0.01	0.018	0.004				0.389	540	355	26	42	170			



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 50421-1030(80278099)
DATE: 2014.12.6
PAGE: 7 OF 8

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.																			
WCB	NORMALIZE	920-940 (1688-1724°F)	1H/25MM	AIR	GAS																				
PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS										MECHANICAL PROPERTIES												
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (Joule)			
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%			HB	TEMP °C	Avg	Min
			MAX	0.23	1.28	0.6	0.03	0.035	0.5	0.5	0.2	0.3	0.03				655					237			
			MIN														485	250	22	35	135				
WEDGE	WCB	61A33	0.2	0.76	0.44	0.017	0.018	0.069	0.024	0.01	0.01	0.001				0.345	510	335	34	59	169				



Certificate of Conformance

Certificate #: P4-136702

Online 600144
Page 1 of 2

Plant 4 Velan Inc.
1010 Cowie Street
Granby, Quebec
Canada, J2J 1E7
Phone : 450-378-2305
Fax : 450-378-6865

Customer Name : MRC CANADA ULC.
Customer Po # : S759225007
Valve Order # : M014-870277-W
Valve Design : API-600
Hydro Test Spec : API-600
Test Result : ACCEPTABLE

NOTES : ALL TESTS AND EXAMINATIONS MEET EN 10204-3.1/ISO 10474-3.1

IT IS THE END USER'S RESPONSIBILITY TO ENSURE THAT MATERIALS ARE SUITABLE FOR THE INTENDED SERVICE.

VALVE(S) MEET(S) NACE MR0175

MATERIAL TEST RESULTS SHOWN BELOW:

CHEMICALS

ASTM Code: A352-06-1C/B/L/C/C.

Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)								
BND51D05	BODY	0.191	0.939	0.029	0.010	0.438	0.030	0.281	0.035	0.005	0.007								
Heat Treatment																			
QUEN & TEMP																			
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)								
BND51D21	BONNET	0.200	0.950	0.030	0.012	0.414	0.029	0.259	0.043	0.005	0.007								
Heat Treatment																			
QUEN & TEMP																			
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)								
BND51F14	BONNET	0.192	0.870	0.027	0.008	0.466	0.033	0.253	0.055	0.010	0.006								
Heat Treatment																			
QUEN & TEMP																			
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)								
BND53D07	BODY	0.187	0.852	0.027	0.009	0.484	0.031	0.252	0.034	0.004	0.006								
Heat Treatment																			
QUEN & TEMP																			
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)								
BND53F11	BODY	0.191	0.888	0.029	0.012	0.391	0.035	0.262	0.041	0.004	0.008								
Heat Treatment																			
QUEN & TEMP																			
Heat Code	Desc	(C)	(Min)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)								
BND54F10	BODY	0.200	0.939	0.031	0.011	0.449	0.037	0.269	0.044	0.004	0.008								
Heat Treatment																			
QUEN & TEMP																			
													Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)		
													600.0 / 87.0	375.0 / 54.4	31.4	60.1	/		
													Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B	GS	
													45.0 / 48.0 / 46.0	-46.0	33.2 / 35.4 / 33.9	-50.8			
													Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)		
													583.0 / 84.6	383.0 / 55.5	29.0	56.0	/		
													Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B	GS	
													41.0 / 45.0 / 42.0	-46.0	30.2 / 33.2 / 31.0	-50.8			
													Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)		
													587.0 / 85.1	395.0 / 57.3	29.4	57.0	/		
													Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B	GS	
													40.0 / 43.0 / 46.0	-46.0	29.5 / 31.7 / 33.9	-50.8			
													Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)		
													578.0 / 83.8	363.0 / 52.6	32.2	61.1	/		
													Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B	GS	
													48.0 / 43.0 / 47.0	-46.0	35.4 / 31.7 / 34.7	-50.8			
													Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)		
													599.0 / 86.9	399.0 / 57.9	29.0	55.0	/		
													Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B	GS	
													42.0 / 48.0 / 44.0	-46.0	31.0 / 35.4 / 32.5	-50.8			
													Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)		
													546.0 / 79.2	346.0 / 50.2	29.8	57.0	/		
													Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B	GS	
													40.0 / 44.0 / 45.0	-46.0	29.5 / 32.5 / 33.2	-50.8			

MECHANICALS [F/B: flattening/ bending; GS: Grain size]

Tag Number(s) : NONE

Certificate Date : 02-JAN-2014
Item Number : 13
Quantity : 14
Figure Number : F08-0064C-31NB-W320
Description : VALVE 2" 150 GATE RF
Draw No. & Rev : REV

Position No : 65

NCLIA - DPH-2001
CPO#144 GF-01600



Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND54F11	BONNET	0.201	0.901	0.030	0.008	0.491	0.032	0.257	0.054	0.011	0.007	594.0 / 86.2	407.0 / 59.0	35.0	59.1	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND55D19	BONNET	0.195	0.853	0.024	0.009	0.407	0.032	0.275	0.039	0.006	0.007	575.0 / 83.4	367.0 / 53.2	29.6	55.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND55F10	BODY	0.192	0.851	0.030	0.007	0.433	0.042	0.266	0.042	0.005	0.012	554.0 / 80.4	363.0 / 52.6	28.8	56.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0.025	0.016	0.476	0.035	0.263	0.033	0.001	0.001	610.0 / 88.5	428.0 / 62.1	35.0	57.0	/
Heat Treatment QUEN & TEMP																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND60G28	BONNET	0.197	0.860	0												

Valian hereby certifies that the valve(s) described above is (are) in conformance with the purchase order and specification requirements. The test report represents the actual attributes of items furnished and all test results are in full conformance with applicable specification and purchase order requirements.

Mikael Bouchard for Manager of Q.C. Documentation	02-JAN-2014 Date
--	---------------------

Customer Representative _____ Date _____



No : 80

Tag Number(s) : NONE

NONE

CHEMICALS

MECHANICALS [F/B: Fatening/ bending; GS: Grain size]

Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND5ID05	BODY	0.191	0.939	0.029	0.010	0.438	0.030	0.281	0.035	0.005	0.007	600.0 / 87.0	375.0 / 54.4	31.4	60.1	/
	Heat Treatment															
	QUEN & TEMP	Impact Energy (J) Temperature (°C) Impact Energy (ft-lb) Temperature (°F) F/B GS														
45.0 / 48.0 / 46.0 33.2 / 35.4 / 33.9 -50.8																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND5ID21	BONNET	0.200	0.950	0.030	0.012	0.414	0.029	0.259	0.043	0.005	0.007	583.0 / 84.6	383.0 / 55.5	29.0	56.0	/
	Heat Treatment															
	QUEN & TEMP	Impact Energy (J) Temperature (°C) Impact Energy (ft-lb) Temperature (°F) F/B GS														
41.0 / 45.0 / 42.0 -46.0 30.2 / 33.2 / 31.0 -50.8																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND5IE02	BONNET	0.195	0.983	0.030	0.006	0.434	0.030	0.264	0.048	0.008	0.012	591.0 / 85.7	395.0 / 57.3	28.4	52.0	/
	Heat Treatment															
	QUEN & TEMP	Impact Energy (J) Temperature (°C) Impact Energy (ft-lb) Temperature (°F) F/B GS														
47.0 / 41.0 / 42.0 -46.0 34.7 / 30.2 / 31.0 -50.8																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND5IF14	BONNET	0.192	0.870	0.027	0.008	0.466	0.033	0.253	0.055	0.010	0.006	587.0 / 85.1	395.0 / 57.3	29.4	57.0	/
	Heat Treatment															
	QUEN & TEMP	Impact Energy (J) Temperature (°C) Impact Energy (ft-lb) Temperature (°F) F/B GS														
40.0 / 43.0 / 46.0 -46.0 29.5 / 31.7 / 33.9 -50.8																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND52F11	BODY	0.201	0.873	0.032	0.008	0.404	0.031	0.251	0.032	0.004	0.007	546.0 / 79.2	346.0 / 50.2	28.6	54.0	/
	Heat Treatment															
	QUEN & TEMP	Impact Energy (J) Temperature (°C) Impact Energy (ft-lb) Temperature (°F) F/B GS														
43.0 / 46.0 / 48.0 -46.0 31.7 / 33.9 / 35.4 -50.8																
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND53F11	BODY	0.191	0.888	0.029	0.012	0.391	0.035	0.262	0.041	0.004	0.008	599.0 / 86.9	399.0 / 57.9	29.0	55.0	/
	Heat Treatment															
	QUEN & TEMP	Impact Energy (J) Temperature (°C) Impact Energy (ft-lb) Temperature (°F) F/B GS														
42.0 / 48.0 / 44.0 -46.0 31.0 / 35.4 / 32.5 -50.8																

Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND54F11	BONNET	0.201	0.901	0.030	0.008	0.491	0.032	0.257	0.054	0.011	0.007	594.0 / 86.2	407.0 / 59.0	35.0	59.1	/
Heat Treatment																
QUEN & TEMP												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
												43.0 / 45.0 / 45.0	-46.0	31.7 / 33.2 / 33.2	-50.8	
Heat Code Desc																
BND55F10	BODY	0.192	0.851	0.030	0.007	0.433	0.042	0.266	0.042	0.005	0.012	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
												554.0 / 80.4	363.0 / 52.6	28.8	56.0	/
Heat Treatment												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
QUEN & TEMP												44.0 / 47.0 / 41.0	-46.0	32.5 / 34.7 / 30.2	-50.8	

Velan hereby certifies that the valve(s) described above is (are) in conformance with the purchase order and specification requirements. The test report represents the actual attributes of items furnished and all test results are in full conformance with applicable specification and purchase order requirements.

Mikael Bouchard for
Manager of Q.C. Documentation
02-JAN_2014
Date
Customer Representative
Date



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 53001-40(80317191)
DATE: 2014-12-6
PAGE: 1 OF 3

CUSTOMER: NEWAY VALVE INTERNATIONAL, INC.-MRM
9757 Stafford Centre Rd., Stafford
USA

QUANTITY: 6
PART NO. 10289143
PRODUCT CODE 3G1RC12-NC-000

PRODUCT DESCRIPTION: GATE VALVE, 3G1RL21/12
-LLC-WEB-GBRJ
GATE VALVE, 3.150LB
ASTM A352 LCC, F316/HF
RAISED FACE END, LOW EMISSION

PURCHASE ORDER: 6003945MRC_S 759 248

PROJECT NAME:	HYDROSTATIC		PNEUM	RESULT	VISUAL	DIMENSION	OPERATION	MARKING
	SHELL	SEATS/BACKSEAT	SEATS	OK	OK	OK	OK	OK
	3.2/464	2.2/319	0.6/87					

APPLICABLE STANDARDS AND SPECIFICATION:

- PT RATING: ASME B16.34
- MAIN MATERIAL: RELEVANT ASTM STANDARD
- DESIGN: API600 ASME B16.34
- TEST: API598 EN12266
- TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL
- VALVES CONFORM TO NACE STANDARD MR.0175 LATEST REVISION

NOTE: ALL RELATED STANDARDS ARE THE LATEST VERSION.

NL1A-DPH-2001
CP0#145 GF-01L00

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order.

NEWAY VALVE

Q.C. Manager



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC No. 53001-40(80317191)
DATE: 2014.12.6
PAGE: 2 OF 3

PRODUCT TRACEABILITY

SERIAL NO.	MATERIAL CODE AND HEAT NO.			SERIAL NO.	MATERIAL CODE AND HEAT NO.			SERIAL NO.	MATERIAL CODE AND HEAT NO.			SERIAL NO.	MATERIAL CODE AND HEAT NO.		
	BODY	BONNET	WEDGE/DISC		BODY	BONNET	WEDGE/DISC		BODY	BONNET	WEDGE/DISC		BODY	BONNET	WEDGE/DISC
53001-040-1	X2880	X1725	6365L	53001-040-2	X2880	X1725	6365L	53001-040-3	X2880	X1725	6365L	53001-040-4	X2880	X1725	6365L
53001-040-5	X2880	X1725	6365L	53001-040-6	X2880	X1725	6365L								



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 53001-40(80317191)
DATE: 2014.12.6
PAGE: 3 OF 3

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace
LCC	NORMALIZE	910-930 (1670-1706°F)	1H/25MM, ≥1.5H	AIR	GAS
LCC	QUENCHED	920-940 (1688-1724°F)	1H/25MM, ≥2.5H	WATER	GAS
LCC	TEMPER	610-630 (1130-1166°F)	4H	AIR	GAS

We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS													MECHANICAL PROPERTIES									
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (JOULE)			
			%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%		HB	TEMP °C	Avg	Min		
		MAX.	0.25	1.2	0.6	0.045	0.04	0.5	0.5	0.2	0.3	0.03				655				237	-50	27.00	22.00		
			MIN.														485	275	22	35	135				
WEDGE BONNET BODY	LCC	6365L	0.218	1.044	0.399	0.013	0.021	0.025	0.013	0.001	0.022	0.003			0.4	525	355	32	65	159	28	29	32		
	LCC	X1725	0.229	1.088	0.382	0.011	0.02	0.044	0.022	0.004	0.022	0.002			0.423	590	435	31	63	170	58	71	64		
	LCC	X2880	0.211	1.081	0.438	0.014	0.026	0.042	0.019	0.005	0.021	0.003			0.404	550	395	33	61	163	50	49	50		



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 36582-350(80139307)
DATE: 2014-12-6
PAGE: 1 OF 4

CUSTOMER	QUANTITY	PART NO.	PRODUCT CODE	PRODUCT DESCRIPTION
----------	----------	----------	--------------	---------------------

NEWAY VALVE INTERNATIONAL, INC-MRM TX 77477 10749 CASH RD. STAFFORD USA	1	10178985	4G3RA8-000	GATE VALVE, 4G3R, C008 (LLC-WEB.) GATE VALVE, 4.300LB ASTM A216 WCB, F6A/HF RAISED FACE END, LOW EMISSION, LOW EMISSION
---	---	----------	------------	---

PURCHASE ORDER:	PRESSURE TEST (Mpa/PSI)			OTHER INSPECTION			

6001275MRC_S75911022	SHELL	HYDROSTATIC	SEATS/BACKSEAT	PNEUM	SEATS	RESULT	VISUAL	DIMENSION	OPERATION	MARKING

PROJECT NAME:	7.8/1131	5.7/827	0.6/87	OK	OK	OK	OK	OK	OK	OK
---------------	----------	---------	--------	----	----	----	----	----	----	----

APPLICABLE STANDARDS AND SPECIFICATION:

- PT RATING: ASME B16.34
- MAIN MATERIAL: RELEVANT ASTM STANDARD
- DESIGN: API600 ASME B16.34
- TEST: API598 EN12266
- TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL

NOTE: ALL RELATED STANDARDS ARE THE LATEST VERSION.

NL1A-DPH-2001
CPO#146 GF-03A00

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order.

WITNESSED BY: _____
NEWAY VALVE
Q.C. Manager



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC No. 36582-350(80139307)
DATE: 2014.12.6
PAGE: 2 OF 4

PRODUCT TRACEABILITY

[illegible]



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 36582-350(80139307)
DATE: 2014.12.6
PAGE: 3 OF 4

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace
CA15	NORMALIZE	1020±10 (1868±50°F)	1H/25MM,≥2H	AIR	GAS FURNACE
CA15	TEMPER	750±10 (1382±50°F)	1H/25MM,≥2.5H	AIR	GAS FURNACE
We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.					

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS													MECHANICAL PROPERTIES									
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (Joule)			
			%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%			HB	TEMP °C	Avg	Min	
			MAX	0.15	1	1.5	0.04	0.04	14	1	0.5							795				286			
			MIN						11.5									620	450	18	30	253			
WEDGE	CA15	5A486	0.13	0.86	0.86	0.01	0.026	12.47	0.18	0.025						730	565	22	52	260					



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 36582-350(80139307)
DATE: 2014.12.6
PAGE: 4 OF 4

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.																			
WCB	NORMALIZE	930±10 (1706±50°F)	1H/25MM	AIR	GAS																				
PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS												MECHANICAL PROPERTIES										
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (JOULE)			
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%			HB	TEMP °C	Avg	Min
		MAX.	0.23	1.28	0.6	0.03	0.035	0.5	0.5	0.2	0.3	0.03					655					237			
		MIN.															485	250	22	35	135				
BODY	WCB	1H736	0.213	1.01	0.399	0.008	0.026	0.038	0.023	0.008	0.024	0.003				0.394	590	405	33	56	167				
BONNET	WCB	1H304	0.203	1.053	0.435	0.007	0.03	0.048	0.017	0.014	0.021	0.002				0.394	585	380	33	57	146				



Certificate of Conformance

Page 1 of 1

Certificate # P4-141943

CP0#147

Plant 4 Velan Inc.
1010 Cowie Street
Granby, Quebec
Canada, J2L 1E7
Phone : 450-378-2305
Fax : 450-378-6865

Customer Name : MRC CANADA ULC.
Customer Po # : S759248808
Velan Order # : M014-87267-W
Valve Design : API-600
Hydro Test Spec : API-600
Test Result : ACCEPTABLE

Certificate Date : 17-SEP-2014
Item Number : 10
Quantity : 3
Figure Number : F14-0064C-31NB
Description : VALVE 6" 150 GATE RF
Draw No. & Rev : REV

Tag Number(s) : NONE

NOTES : ALL TESTS AND EXAMINATIONS MEET EN 10204-3.1/ ISO 10474-3.1

IT IS THE END USER'S RESPONSIBILITY TO ENSURE THAT MATERIALS ARE SUITABLE FOR THE INTENDED SERVICE.

VALVE(S) WERE CLEANED, INSPECTED, PACKAGED AND LABELLED IN COMPLIANCE VEL-QCI-1794, REVISION 6 FOR OXYGEN SERVICE P

MATERIAL TEST RESULTS SHOWN BELOW:

CHEMICALS

MECHANICALS [F/B: Flattening/ bending; GS: Grain size]

ASTM Code: A352-06-LCB/LCC-

Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNE52B27	BONNET	0.191	0.928	0.025	0.009	0.442	0.028	0.279	0.038	0.004	0.007	574.0 / 83.3	399.0 / 57.9	32.0	57.0	/
Heat Treatment	QUEN & TEMP											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
												43.0 / 46.0 / 42.0	-46.0	31.7 / 33.9 / 31.0	-50.8	
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNE53B26	BODY	0.197	0.867	0.031	0.010	0.470	0.031	0.265	0.042	0.005	0.006	591.0 / 85.7	407.0 / 59.0	31.0	58.0	/
Heat Treatment	QUEN & TEMP											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
												45.0 / 43.0 / 44.0	-46.0	33.2 / 31.7 / 32.5	-50.8	
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNE55C02	BODY	0.192	0.947	0.026	0.008	0.415	0.037	0.285	0.040	0.005	0.006	505.0 / 73.2	326.0 / 47.3	33.0	62.0	/
Heat Treatment	QUEN & TEMP											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
												42.0 / 43.0 / 43.0	-46.0	31.0 / 31.7 / 31.7	-50.8	
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BNE58C01	BONNET	0.192	0.900	0.028	0.009	0.440	0.037	0.272	0.043	0.005	0.007	560.0 / 81.2	350.0 / 50.8	31.0	57.0	/
Heat Treatment	QUEN & TEMP											Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
												45.0 / 42.0 / 49.0	-46.0	33.2 / 31.0 / 36.1	-50.8	

Velan hereby certifies that the valve(s) described above is (are) in conformance with the purchase order and specification requirements. The test report represents the actual attributes of items furnished and all test results are in full conformance with applicable specification and purchase order requirements.

Bill Bratt
Gilles Guerin for

Velan

Date

17-SEP-2014

Customer Representative

Date

VELAN-DPH-2001
CP0#147 GF-01L00



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 37685-50(80151042)

DATE: 2014-12-6

PAGE: 1 OF 4

CUSTOMER

NEWAY VALVE INTERNATIONAL, INC-MRM
TX 77477 10749 CASH RD. STAFFORD
USA

QUANTITY

1

PART NO.

10678522

PRODUCT CODE

8G1RA8-G-000

PRODUCT DESCRIPTION

GATE VALVE 8G1R-G, C008
[BA00-LLC-WEB, GBR]
GATE VALVE, 8" 150LB
ASTM A216 WCB, F6A/HF
RAISED FACE END, GEAR OPERATED, LOW EMISSION GEAR
OPERATED, LOW EMISSION

PURCHASE ORDER:

6001659MRC-S75912423

PRESSURE TEST (Mpa/Psi)

OTHER INSPECTION

PROJECT NAME:

SHELL

SEATS/BACKSEAT

SEATS

OK

OK

OK

OK

OK

3.2/464

2.2/319

0.6/87

APPLICABLE STANDARDS AND SPECIFICATION:

- P/T RATING: ASME B16.34
- MAIN MATERIAL: RELEVANT ASTM STANDARD
- DESIGN: API600 ASME B16.34
- TEST: API598 EN12266
- TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL

NOTE: ALL RELATED STANDARDS ARE THE LATEST VERSION.

NL1A-DPH-2001
CPD#149 GF-D1A20

WITNESSED BY: _____

Q.C. Manager

Tian Lee

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order.

NEWAY VALVE



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 37685-50(80151042)
DATE: 2014.12.6
PAGE: 3 OF 4

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.																			
CA15	NORMALIZE	1020±10 (1868±50°F)	1H/25MM,≥2H	AIR	GAS FURNACE																				
CA15	TEMPER	750±10 (1382±50°F)	1H/25MM,≥2.5H	AIR	GAS FURNACE																				
PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS												MECHANICAL PROPERTIES										
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (JOULE)			
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%			HB	TEMP °C	Avg	Min
			MAX.	0.15	1	1.5	0.04	0.04	14	1	0.5						795					286			
			MIN.						11.5								620	450	18	30	253				
WEDGE	CA15	7A426	0.12	0.78	0.83	0.01	0.024	12.55	0.143	0.01							704	505	21	49	262				



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 37685-50(80151042)
DATE: 2014.12.6
PAGE: 4 OF 4

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace
WCB	NORMALIZE	930±10 (1706±50°F)	1H/25MM	AIR	GAS

We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS													MECHANICAL PROPERTIES									
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (JOULE)			
			%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%			HB	TEMP °C	Avg	Min	
		MAX.	0.23	1.28	0.6	0.03	0.035	0.5	0.5	0.2	0.3	0.03				655					237				
			MIN.														485	250	22	35	135				
BONNET	WCB	5H023	0.198	1.068	0.441	0.01	0.024	0.04	0.03	0.016	0.036	0.005			0.393	585	390	32	53	156					
BODY	WCB	5H392	0.209	0.976	0.405	0.012	0.026	0.035	0.027	0.011	0.027	0.003			0.385	580	370	33	59	170					



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 47219-180(80244350)

DATE: 2014-12-6

PAGE: 1 OF 8

CUSTOMER

QUANTITY

PART NO.

PRODUCT CODE

PRODUCT DESCRIPTION

NEWAY VALVE INTERNATIONAL, INC-MRM
9757 Stafford Centre Rd., Stafford
USA
USA

8

10460982

10G3RA8-G

GATE VALVE, 10G3R-A, CO0/8
[BAOC-LLC-OF3S-WEB]
GATE VALVE, 10,300LB
ASTM A216 WCB, F6A/HF

RAISED FACE END, GEAR OPERATED, LOW EMISSION

PURCHASE ORDER:

6003058MRC_S 78H 211

PRESSURE TEST (Mpa/PSI)

OTHER INSPECTION

PROJECT NAME:

SHELL

SEATS/BACKSEAT

SEATS

OK

OK

OK

OK

OK

7.8/1131

5.7/827

0.6/87

APPLICABLE STANDARDS AND SPECIFICATION:

- P/T RATING: ASME B16.34
- MAIN MATERIAL: RELEVANT ASTM STANDARD
- DESIGN: API600 ASME B16.34
- TEST: API598 EN12286
- TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL

NOTE: ALL RELATED STANDARDS ARE THE LATEST VERSION.

NCLA-DPH-2001
CPO#151 GF-03A00

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order.

NEWAY VALVE

Q.C. Manager

Tian Lee

WITNESSED BY:



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC No. 47219-180(80244350)
DATE: 2014.12.6
PAGE: 2 OF 8

PRODUCT TRACEABILITY

SERIAL NO.	MATERIAL CODE AND HEAT NO.			SERIAL NO.	MATERIAL CODE AND HEAT NO.			SERIAL NO.	MATERIAL CODE AND HEAT NO.			SERIAL NO.	MATERIAL CODE AND HEAT NO.		
	BODY	BONNET	WEDGE/DISC		BODY	BONNET	WEDGE/DISC		BODY	BONNET	WEDGE/DISC		BODY	BONNET	WEDGE/DISC
47219-180-1	F0965	F2443	44A24	47219-180-2	F0960	F2443	44A26	47219-180-3	F1091	F2755	44A23	47219-180-4	F0892	F2698	44A27
47219-180-5	F1105	F2666	44A30	47219-180-6	F1091	F2296	44A30	47219-180-7	F1481	F2711	44A27	47219-180-8	F1819	F2699	44A26



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 47219-180(80244350)
DATE: 2014.12.6
PAGE: 4 OF 8

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.																			
A105N	NORMALIZE	850~920 (1562~1688°F)	1H/25MM≥1H	AIR	ELECTRIC FURNACE																				
PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS										MECHANICAL PROPERTIES												
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (Joule)			
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%			HB	TEMP °C	Avg	Min
		MAX.	0.35	1.05	0.35	0.04	0.035	0.3	0.4	0.12	0.4	0.08										187			
		MIN.		0.6	0.1												485	250	22	30					
SEAT RING	A105N	YXCE102	0.21	0.94	0.21	0.012	0.015	0.04	0.02	0.02	0.04	0.02					0.387	505	330	29	63	152			



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 47219-180(80244350)
DATE: 2014.12.6
PAGE: 5 OF 8

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.																		
B7	QUENCH		1H/25MM ≥1H	OIL	ELECTRIC																			
B7	TEMPER		1H/25MM ≥1H	AIR	GAS OR ELECTRIC																			
PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS												MECHANICAL PROPERTIES									
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (JOULE)		
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%		HB	TEMP °C	Avg	Min
		MAX	0.49	1.1	0.35	0.04	0.035	1.2		0.25											321			
		MIN	0.37	0.65	0.15			0.75		0.15							860	720	16	50				
BOLT	B7	ADF007	0.4	0.76	0.21	0.009	0.017	0.96		0.165							920	828	19	56	270			



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 47219-180(80244350)
DATE: 2014.12.6
PAGE: 6 OF 8

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.
F6A-II	NORMALIZE	980 ~1050 (Nan-1922°F)	1H/25MM, ≥1H	AIR	ELECTRIC	
F6A-II	TEMPER	≥675 (≥167°F)	1H/25MM, ≥1H	AIR	GAS OR ELECTRIC	

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS														MECHANICAL PROPERTIES							
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (Joule)		
			%	%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%		HB	TEMP °C	Avg	Min
			MAX.	0.15	1	1	0.03	0.04	13.5	0.5											229			
			MIN.						11.5								585	380	18	35	167			
STEM	F6A-II	DDA035	0.13	0.38	0.44	0.01	0.026	11.9	0.16								606	398	19	38	219			



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 47219-180(80244350)
DATE: 2014.12.6
PAGE: 7 OF 8

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.
WCB	NORMALIZE	920-940 (1668-1724°F)	1H/25MM	AIR	GAS	

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS													MECHANICAL PROPERTIES									
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (Joule)			
			%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%			HB	TEMP °C	Avg	Min	
		MAX.	0.23	1.28	0.6	0.03	0.035	0.5	0.5	0.2	0.3	0.03				655					237				
		MIN.														485	250	22	35	135					

BONNET	WCB	F2296	0.182	0.989	0.41	0.007	0.019	0.089	0.029	0.008	0.014	0.003				0.37	500	325	28	45	159				
BONNET	WCB	F2755	0.183	0.997	0.403	0.007	0.021	0.118	0.04	0.014	0.021	0.005				0.381	515	320	30	62	159				
BODY	WCB	F0892	0.197	1.042	0.432	0.01	0.026	0.126	0.039	0.021	0.023	0.004				0.405	530	360	27	47	163				
BODY	WCB	F1481	0.193	1.038	0.435	0.007	0.007	0.105	0.032	0.011	0.017	0.004				0.393	535	355	27	46	163				
WEDGE	WCB	44A24	0.2	0.82	0.48	0.017	0.015	0.067	0.03	0.011	0.036	0.001				0.357	530	335	36	64	167				
BONNET	WCB	F2443	0.191	0.976	0.54	0.01	0.023	0.262	0.089	0.025	0.021	0.006				0.42	565	405	27	46	170				
BODY	WCB	F1105	0.193	0.967	0.397	0.007	0.02	0.264	0.06	0.029	0.021	0.007				0.42	555	370	30	47	179				
BODY	WCB	F1819	0.197	1.036	0.42	0.008	0.021	0.116	0.044	0.021	0.015	0.003				0.402	510	320	30	56	163				
WEDGE	WCB	44A26	0.2	0.8	0.48	0.014	0.021	0.046	0.017	0.011	0.021	0.001				0.347	570	410	30	66	166				
BODY	WCB	F1091	0.183	1.084	0.458	0.006	0.018	0.082	0.026	0.008	0.016	0.005				0.385	535	370	30	46	170				
BODY	WCB	F0965	0.204	0.994	0.384	0.007	0.026	0.111	0.034	0.014	0.022	0.004				0.399	515	330	31	48	163				
WEDGE	WCB	44A27	0.2	0.9	0.5	0.011	0.01	0.118	0.014	0.01	0.027	0.001				0.379	545	365	30	59	172				
BONNET	WCB	F2711	0.183	1.026	0.452	0.01	0.025	0.143	0.04	0.02	0.023	0.005				0.392	520	340	27	55	163				



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 47219-180(80244350)
DATE: 2014.12.6
PAGE: 8 OF 8

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace
WCB	NORMALIZE	920-940 (1688-1724°F)	1H/25MM	AIR	GAS

We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS													MECHANICAL PROPERTIES									
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (J/OULE)			
			%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%			HB	TEMP °C	Avg	Min	
		MAX.	0.23	1.28	0.6	0.03	0.035	0.5	0.5	0.2	0.3	0.03				655					237				
			MIN.														485	250	22	35	135				
BONNET	WCB	F2699	0.192	1.032	0.435	0.009	0.025	0.118	0.047	0.01	0.018	0.004				0.395	535	350	30	52	167				
BONNET	WCB	F2666	0.189	0.988	0.388	0.009	0.022	0.105	0.043	0.009	0.016	0.005				0.381	525	335	31	55	170				
WEDGE	WCB	44A30	0.19	0.81	0.44	0.011	0.023	0.159	0.02	0.016	0.014	0.001				0.362	530	350	34	68	174				
BODY	WCB	F0960	0.203	0.98	0.415	0.009	0.027	0.218	0.063	0.032	0.037	0.005				0.424	535	330	34	48	170				
WEDGE	WCB	44A23	0.19	0.8	0.48	0.018	0.014	0.111	0.036	0.011	0.03	0.001				0.352	550	390	32	60	172				
BONNET	WCB	F2698	0.2	1.052	0.472	0.008	0.022	0.106	0.033	0.007	0.015	0.004				0.402	535	340	26	47	163				



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC NO. 48489-790(80252017)
DATE: 2014-12-6
PAGE: 1 OF 4

CUSTOMER	QUANTITY	PART NO.	PRODUCT CODE	PRODUCT DESCRIPTION
----------	----------	----------	--------------	---------------------

NEWAY VALVE INTERNATIONAL, INC.-MRM 9757 Stafford Centre Rd., Stafford USA USA	1	10689933	2G1RA8-000	GATE VALVE 2G1R V3 C00/8 [LLC-WEB.-GBR] GATE VALVE 2.150LB ASTM A216 WCB, F6A/HF RAISED FACE END, LOW EMISSION
---	---	----------	------------	--

PURCHASE ORDER:	PRESSURE TEST (Mpa/PSI)			OTHER INSPECTION			
-----------------	-------------------------	--	--	------------------	--	--	--

6003239MRC_S 78H 218

PROJECT NAME:	HYDROSTATIC		PNEUM	RESULT	VISUAL	DIMENSION	OPERATION	MARKING
	SHELL	SEATS/BACKSEAT	SEATS					

3.2/464		2.2/319	0.6/87	OK	OK	OK	OK	OK
---------	--	---------	--------	----	----	----	----	----

APPLICABLE STANDARDS AND SPECIFICATION:

- P/T RATING: ASME B16.34
- MAIN MATERIAL: RELEVANT ASTM STANDARD
- DESIGN: API600 ASME B16.34
- TEST: API598 EN12286
- TRIM MATERIAL (SEAT/STEM) AND BOLTING ARE ACCORDING TO THE P.O. AND MATERIAL

NOTE: ALL RELATED STANDARDS ARE THE LATEST VERSION.

2L1A-DPH-2001
CPO#156 GF-01A200

We hereby certify that the valves listed above are manufactured and tested in accordance with the requirements of valve standard and purchase order.

WITNESSED BY: _____

NEWAY VALVE
Q.C. Manager



MATERIAL TEST REPORT

EN 10204 2004-3.1

TC No. 48489-790(80252017)

DATE: 2014.12.6

PAGE: 2 OF 4

PRODUCT TRACEABILITY

[illegible]



MATERIAL TEST REPORT


EN 10204 2004-3.1

TC NO. 48489-790(80252017)
DATE: 2014.12.6
PAGE: 3 OF 4

MATERIAL COMPONENTS AND PROPERTIES:

Material	Heat treatment	Temp. °C(°F)	Holding time(h)	Cooling media	Furnace	We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.
CA15	NORMALIZE	1020±10 (1868±50°F)	1H/25MM ≥2H	AIR	GAS FURNACE	
CA15	TEMPER	670±10 (1238±50°F)	1H/25MM ≥2.5H	AIR	GAS FURNACE	

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS													MECHANICAL PROPERTIES									
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (Joule)			
			%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%		HB	TEMP °C	Avg	Min		
			MAX.	0.15	1	1.5	0.04	0.04	14	1	0.5					795					286				
			MIN.						11.5								620	450	18	30	253				
WEDGE	CA15	31A39	0.14	0.9	1.03	0.01	0.03	13	0.113	0.015						742	531	21	50	259					



We hereby certify that the material are manufactured, inspected and tested in accordance with the material specification and purchase order requirements.

PART NAME	MATERIAL	HEAT NO.	CHEMICAL ANALYSIS													MECHANICAL PROPERTIES									
			C	Mn	Si	S	P	Cr	Ni	Mo	Cu	V	Al	Nb	Fe	C.E.	TS	YS	E	R	HARD	IMPACT TEST (Joule)			
			%	%	%	%	%	%	%	%	%	%	%	%		Mpa	Mpa	%		HB	TEMP °C	Avg	Min		
		MAX.	0.23	1.28	0.6	0.03	0.035	0.5	0.5	0.2	0.3	0.03				655				237					
		MIN														485	250	22	35	135					

Address: No. 999 Xinagiang Road Suzhou New District, China Tel: 86-512-6666-51365 Fax: 86-512-6666-51360 <http://www.newayvalve.com>



Certificate of Conformance

Certificate #: P4-139239

Page 1 of 2
CP# 157

Plant 4 Velan Inc.
1010 Cowie Street
Granby, Quebec
Canada, J2J 1E7
Phone : 450-378-2305
Fax : 450-378-6865

Customer Name : MRC CANADA ULC.
Customer Po # : S759248808
Velan Order # : M014-872767-W
Valve Design : API-600
Hydro Test Spec : API-600
Test Result : ACCEPTABLE

NOTES : ALL TESTS AND EXAMINATIONS MEET EN 10204-3.1 / ISO 10474-3.1

IT IS THE END USER'S RESPONSIBILITY TO ENSURE THAT MATERIALS ARE SUITABLE FOR THE INTENDED SERVICE.

VALVES MEET THE MATERIAL REQUIREMENTS OF CURRENT NACE MR0103 & NACE MR0175 / ISO 15156.

MATERIAL TEST RESULTS SHOWN BELOW:

CHEMICALS

ASTM Code: A352-06-FCB/LCC.

Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)
BND51L26	BODY	0.195	0.920	0.033	0.009	0.478	0.033	0.266	0.042	0.007	0.007
Heat Treatment											
QUEN & TEMP											
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)
BND51L28	BONNET	0.194	0.947	0.030	0.008	0.410	0.035	0.286	0.042	0.007	0.007
Heat Treatment											
QUEN & TEMP											
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)
BND51L29	BONNET	0.192	0.944	0.029	0.008	0.404	0.035	0.282	0.042	0.007	0.007
Heat Treatment											
QUEN & TEMP											
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)
BND51L26	BONNET	0.191	0.954	0.024	0.007	0.452	0.037	0.274	0.051	0.009	0.008
Heat Treatment											
QUEN & TEMP											
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)
BND51L27	BODY	0.187	0.939	0.028	0.013	0.468	0.036	0.260	0.041	0.006	0.005
Heat Treatment											
QUEN & TEMP											
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)
BND51L27	BONNET	0.187	0.939	0.028	0.013	0.468	0.036	0.260	0.041	0.006	0.005
Heat Treatment											
QUEN & TEMP											

Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
579.0 / 84.0	395.0 / 57.3	33.0	61.0	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
43.0 / 52.0 / 43.0	-46.0	31.7 / 38.4 / 31.7	-50.8	
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
585.0 / 84.8	412.0 / 59.8	33.0	61.0	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
62.0 / 47.0 / 51.0	-46.0	45.7 / 34.7 / 37.6	-50.8	
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
584.0 / 84.7	412.0 / 59.8	31.0	58.0	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
44.0 / 57.0 / 61.0	-46.0	32.5 / 42.0 / 45.0	-50.8	
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
589.0 / 85.4	387.0 / 56.1	33.2	61.1	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
42.0 / 47.0 / 42.0	-46.0	31.0 / 34.7 / 31.0	-50.8	
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
574.0 / 83.3	392.0 / 56.9	31.0	61.0	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
72.0 / 81.0 / 64.0	-46.0	53.1 / 59.7 / 47.2	-50.8	
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
574.0 / 83.3	392.0 / 56.9	31.0	61.0	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
72.0 / 81.0 / 64.0	-46.0	53.1 / 59.7 / 47.2	-50.8	

MECHANICALS [F/B: Flattening/ bending; GS: Grain size]

Certificate Date : 29-APR-2014
Item Number : 08
Quantity : 8
Figure Number : F08-0064C-31NB-W320
Description : VALVE 2" 150 GATE RF
Draw No. & Rev : REV

Tag Number(s) : NONE

NL1A-DPH-2001
CP# 157 GF-01L00

Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND53L27	BODY	0.191	0.878	0.028	0.008	0.398	0.034	0.259	0.051	0.005	0.009	596.0 / 86.4	416.0 / 60.3	31.0	61.0	/
Heat Treatment																
QUEN & TEMP												67.0 / 90.0 / 53.0	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
													-46.0	49.4 / 66.4 / 39.1	-50.8	
Heat Treatment																
QUEN & TEMP												43.0 / 49.0 / 44.0	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
													344.0 / 49.9	33.2	61.1	/
Heat Treatment																
QUEN & TEMP												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
													-46.0	31.7 / 36.1 / 32.5	-50.8	
Heat Code Desc																
BND54L27	BONNET	0.193	0.892	0.029	0.011	0.425	0.034	0.259	0.040	0.006	0.006	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
												606.0 / 87.9	424.0 / 61.5	31.0	61.0	/
Heat Treatment																
QUEN & TEMP												Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
												57.0 / 50.0 / 51.0	-46.0	42.0 / 36.9 / 37.6	-50.8	

Velan hereby certifies that the valve(s) described above is (are) in conformance with the purchase order and specification requirements. The test report represents the actual attributes of items furnished and all test results are in full conformance with applicable specification and purchase order requirements.

Kelly Delafontaine

Gilles Delafontaine for

Velan

Date

29-APR_2014

Customer Representative

Date



Certificate of Conformance

Page 1 Of 2

Certificate #: P4-139517

Plant 4 Velan Inc.
1010 Cowie Street
Granby, Quebec
Canada, J2J 1E7
Phone : 450-378-2305
Fax : 450-378-6865

Customer Name : MRC CANADA ULC.
Customer Po # : S759258276
Velan Order # : M014-874039-W
Valve Design : API-600
Hydro Test Spec : API-600
Test Result : ACCEPTABLE

NOTES : ALL TESTS AND EXAMINATIONS MEET EN 10204-3.1/ISO 10474-3.1

IT IS THE END USERS RESPONSIBILITY TO ENSURE THAT MATERIALS ARE SUITABLE FOR THE INTENDED SERVICE.

VALVES MEET THE MATERIAL REQUIREMENTS OF CURRENT NACE MR0103 & NACE MR0175 / ISO 15156.

CHEMICALS

ASTM Code: A352-06-LCBALCC-

Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)
BND51L26	BODY	0.195	0.920	0.033	0.009	0.478	0.033	0.266	0.042	0.007	0.007
Heat Treatment											
QUEN & TEMP											
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)
BND51L27	BODY	0.190	0.889	0.030	0.010	0.426	0.034	0.257	0.040	0.006	0.006
Heat Treatment											
QUEN & TEMP											
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)
BND51L28	BONNET	0.194	0.947	0.030	0.008	0.410	0.035	0.286	0.042	0.007	0.007
Heat Treatment											
QUEN & TEMP											
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)
BND51L29	BONNET	0.192	0.944	0.029	0.008	0.404	0.035	0.282	0.042	0.007	0.007
Heat Treatment											
QUEN & TEMP											
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)
BND52L26	BODY	0.191	0.954	0.024	0.007	0.452	0.037	0.274	0.051	0.009	0.008
Heat Treatment											
QUEN & TEMP											
Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)
BND52L27	BODY	0.187	0.939	0.028	0.013	0.468	0.036	0.260	0.041	0.006	0.005
Heat Treatment											
QUEN & TEMP											

Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
570.0 / 84.0	395.0 / 57.3	33.0	61.0	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
43.0 / 52.0 / 43.0	-46.0	31.7 / 38.4 / 31.7	-50.8	
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
597.0 / 86.6	416.0 / 60.3	33.0	58.0	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
77.0 / 77.0 / 49.0	-46.0	56.8 / 56.8 / 36.1	-50.8	
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
585.0 / 84.8	412.0 / 59.8	33.0	61.0	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
62.0 / 47.0 / 51.0	-46.0	45.7 / 34.7 / 37.6	-50.8	
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
584.0 / 84.7	412.0 / 59.8	31.0	58.0	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
44.0 / 57.0 / 61.0	-46.0	33.5 / 42.0 / 45.0	-50.8	
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
589.0 / 85.4	387.0 / 56.1	33.2	61.1	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
42.0 / 47.0 / 42.0	-46.0	31.0 / 34.7 / 31.0	-50.8	
Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area (%)	Hardness (HB)
574.0 / 83.3	392.0 / 56.9	31.0	61.0	/
Impact Energy (J)	Temperature (°C)	Impact Energy (ft-lb)	Temperature (°F)	F/B GS
72.0 / 81.0 / 64.0	-46.0	53.1 / 59.7 / 47.2	-50.8	

Certificate Date : 13-MAY-2014
Item Number : 06
Quantity : 12
Figure Number : F08-0064C-3INB-W320
Description : VALVE 2" 150 GATE RF
Draw No. & Rev : REV

Tag Number(s) : NONE

MECHANICALS [F/B: flattening/ bending; GS: Grain size]

Heat Code	Desc	(C)	(Mn)	(P)	(S)	(Si)	(Cu)	(Ni)	(Cr)	(Mo)	(V)	Tensile (MPa / ksi)	Yield (MPa / ksi)	Elongation (%)	Reduction of Area(%)	Hardness (HB)
BND5L28	BONNET	0.193	0.910	0.025	0.009	0.397	0.029	0.260	0.037	0.004	0.007	593.0 / 86.0	428.0 / 62.1	31.0	58.0	/
Heat Treatment																
QUEN & TEMP												71.0 / 47.0 / 39.0	-46.0	52.4 / 34.7 / 28.8	-50.8	F/B GS
Heat Treatment																
BND5L27	BODY	0.191	0.878	0.028	0.008	0.398	0.034	0.259	0.051	0.005	0.009	596.0 / 86.4	416.0 / 60.3	31.0	61.0	/
Heat Treatment																
QUEN & TEMP												67.0 / 90.0 / 53.0	-46.0	49.4 / 66.4 / 39.1	-50.8	F/B GS
Heat Treatment																
BND5L27	BONNET	0.193	0.892	0.029	0.011	0.425	0.034	0.259	0.040	0.006	0.006	606.0 / 87.9	424.0 / 61.5	31.0	61.0	/
Heat Treatment																
QUEN & TEMP												57.0 / 50.0 / 51.0	-46.0	42.0 / 36.9 / 37.6	-50.8	F/B GS
Heat Treatment																
BND5M02	BONNET	0.192	0.935	0.026	0.006	0.428	0.032	0.263	0.044	0.005	0.007	592.0 / 85.9	400.0 / 58.0	34.2	60.1	/
Heat Treatment																
QUEN & TEMP												46.0 / 43.0 / 43.0	-46.0	33.9 / 31.7 / 31.7	-50.8	F/B GS

Velan hereby certifies that the valve(s) described above is (are) in conformance with the purchase order and specification requirements. The test report represents the actual attributes of items furnished and all test results are in full conformance with applicable specification and purchase order requirements.

Daniel Ouellette for
Manager of Q.C. Documentation

13-MAY-2014
Date

Customer Representative
Date